

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 July 2002 (18.07.2002)

PCT

(10) International Publication Number
WO 02/055059 A2

(51) International Patent Classification⁷: **A61K 9/10**,
31/496

(21) International Application Number: PCT/US01/49737

(22) International Filing Date:
20 December 2001 (20.12.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/258,160 22 December 2000 (22.12.2000) US
09/874,799 5 June 2001 (05.06.2001) US
09/874,637 5 June 2001 (05.06.2001) US
09/874,499 5 June 2001 (05.06.2001) US
09/953,979 17 September 2001 (17.09.2001) US
10/035,821 19 October 2001 (19.10.2001) US
10/021,692 12 December 2001 (12.12.2001) US

(71) Applicant: **BAXTER INTERNATIONAL INC.**
[US/US]; One Baxter Parkway, Deerfield, IL 60015 (US).

(72) Inventors: **KIPP, James, E.**; 609 Hermosa Avenue,
Wauconda, IL 60084 (US). **WONG, Joseph, Chung,**
Tak; 36141 N. Bridlewood Avenue, Gurnee, IL 60031
(US). **DOTY, Mark, J.**; 610 Kenilworth, Grayslake, IL
60030 (US). **REBBECK, Christine, L.**; 525 Eagle Ridge

Lane, Algonquin, IL 60102 (US). **BRYNJELSEN, Sean**;
4 Walnut Grove Ct., Lake-In-The-Hills, IL 60156 (US).
WERLING, Jane; 605 S. Highland, Arlington Heights,
IL 60005 (US). **SRIRAM, Rajaram**; 3014 Knollwood,
Glenview, IL 60025 (US).

(74) Agent: **BUONAIUTO, Mark, J.**; Baxter International
Inc., One Baxter Parkway, Deerfield, IL 60015 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI,
SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA,
ZW.

(84) Designated States (*regional*): European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE, TR).

Published:

— *without international search report and to be republished
upon receipt of that report*

*For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.*

(54) Title: METHOD FOR PREPARING SUBMICRON PARTICLE SUSPENSIONS

(57) Abstract: The present invention provides a method for preparing a suspension of a pharmaceutically-active compound, the solubility of which is greater in a water-miscible first organic solvent than in a second solvent which is aqueous. The process includes the steps of : (i) dissolving a first quantity of the pharmaceutically-active compound in the water-miscible first organic solvent to form a first solution ; (ii) mixing the first solution with the second solvent to precipitate the pharmaceutically-active compound ; and (iii) seeding the first solution or the second solvent or the presuspension.

WO 02/055059 A2



P59

(2)

METHOD FOR PREPARING SUBMICRON PARTICLE SUSPENSIONS**DESCRIPTION****CROSS-REFERENCE TO RELATED APPLICATION:**

Not Applicable.

FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT:

5 Not Applicable.

BACKGROUND OF THE INVENTION:**Technical Field**

10 The present invention relates to the preparation of a pharmaceutically active compound. More particularly the invention relates to the manufacture of nanosuspensions of the pharmaceutically active compound for parenteral or oral delivery.

Background Art

15 There is an ever increasing number of pharmaceutical drugs being formulated that are poorly soluble or insoluble in aqueous solutions. Such drugs provide challenges to delivering them in an injectable form such as through parenteral administration. Drugs that are insoluble in water can have significant benefits when formulated as a stable suspension of sub-micron particles. Accurate control of particle size is essential for safe and efficacious use of these formulations. Particles must be less than seven microns in diameter to safely pass through capillaries without causing emboli (Allen et al., 1987; Davis and Taube, 1978; Schroeder et al., 1978; Yokel et al., 1981).

20 One approach to delivering an insoluble drug is disclosed in United States Patent No. 2,745,785. This patent discloses a method for preparing crystals of penicillin G suitable for parenteral administration. The method includes the step of recrystallizing the penicillin G from a formamide solution by adding water to reduce the solubility of the penicillin G. The '785 Patent further provides that the penicillin G particles can be coated with wetting agents such as lecithin, or emulsifiers, surface-
25 active and defoaming agents, or partial higher fatty acid esters of sorbitan or polyoxyalkylene derivatives thereof, or aryl alkyl polyether alcohols or salts thereof. The '785 patent further discloses micronizing the penicillin G with an air blast under pressure to form crystals ranging from about 5 to 20 microns.

30 Another approach is disclosed in United States Patent No. 5,118,528 which discloses a process for preparing nanoparticles. The process includes the steps of: (1) preparing a liquid phase of a

substance in a solvent or a mixture of solvents to which may be added one or more surfactants, (2) preparing a second liquid phase of a non-solvent or a mixture of non-solvents, the non-solvent is miscible with the solvent or mixture of solvents for the substance, (3) adding together the solutions of (1) and (2) with stirring; and (4) removing of unwanted solvents to produce a colloidal suspension of nanoparticles. The '528 Patent discloses that it produces particles of the substance smaller than 500 nm without the supply of energy. In particular the '528 Patent states that it is undesirable to use high energy equipment such as sonicators and homogenizers.

United States Patent No. 4,826,689 discloses a method for making uniformly sized particles from water-insoluble drugs or other organic compounds. First, a suitable solid organic compound is dissolved in an organic solvent, and the solution can be diluted with a non-solvent. Then, an aqueous precipitating liquid is infused, precipitating non-aggregated particles with substantially uniform mean diameter. The particles are then separated from the organic solvent. Depending on the organic compound and the desired particle size, the parameters of temperature, ratio of non-solvent to organic solvent, infusion rate, stir rate, and volume can be varied according to the invention. The '689 Patent discloses this process forms a drug in a metastable state which is thermodynamically unstable and which eventually converts to a more stable crystalline state. The '689 Patent discloses trapping the drug in a metastable state in which the free energy lies between that of the starting drug solution and the stable crystalline form. The '689 Patent discloses utilizing crystallization inhibitors (e.g., polyvinylpyrrolidinone) and surface-active agents (e.g., poly(oxyethylene)-co-oxypropylene) to render the precipitate stable enough to be isolated by centrifugation, membrane filtration or reverse osmosis.

In U.S. Patent Nos. 5,091,188; 5,091,187 and 4,725,442 which disclose (a) either coating small drug particles with natural or synthetic phospholipids or (b) dissolving the drug in a suitable lipophilic carrier and forming an emulsion stabilized with natural or semisynthetic phospholipids. One of the disadvantages of these approaches is they rely on the quality of the raw material of the drug and do not disclose steps of changing the morphology of the raw material to render the material in a friable, more easily processed form.

Another approach to providing insoluble drugs for parenteral delivery is disclosed in U.S. Patent No. 5,145,684. The '684 Patent discloses the wet milling of an insoluble drug in the presence of a surface modifier to provide a drug particle having an average effective particle size of less than 400 nm. The '684 Patent emphasizes the desirability of not using any solvents in its process. The '684 Patent discloses the surface modifier is adsorbed on the surface of the drug particle in an amount sufficient to prevent agglomeration into larger particles.

Yet another attempt to provide insoluble drugs for parenteral delivery is disclosed in U.S. Patent Nos. 5,922,355. The '355 Patent discloses providing submicron sized particles of insoluble drugs using a combination of surface modifiers and a phospholipid followed by particle size reduction using techniques such as sonication, homogenization, milling, microfluidization, precipitation or

recrystallization. There is no disclosure in the '355 Patent of changing process conditions to make crystals in a more friable form.

United States Patent No. 5,780,062 discloses a method of preparing small particles of insoluble drugs by (1) dissolving the drug in a water-miscible first solvent, (2) preparing a second solution of a polymer and an amphiphile in an aqueous second solvent in which the drug is substantially insoluble whereby a polymer/amphiphile complex is formed and (3) mixing the solutions from the first and second steps to precipitate an aggregate of the drug and polymer/amphiphile complex.

United States Patent No. 5,858,410 discloses a pharmaceutical nanosuspension suitable for parenteral administration. The '410 patent discloses subjecting at least one solid therapeutically active compound dispersed in a solvent to high pressure homogenization in a piston-gap homogenizer to form particles having an average diameter, determined by photon correlation spectroscopy (PCS) of 10 nm to 1000 nm, the proportion of particles larger than 5 μ m in the total population being less than 0.1% (number distribution determined with a Coulter counter), without prior conversion into a melt, wherein the active compound is solid at room temperature and is insoluble, only sparingly soluble or moderately soluble in water, aqueous media and/or organic solvents. The Examples in the '410 Patent disclose jet milling prior to homogenization.

United States Patent No. 4,997,454 discloses a method for making uniformly sized particles from solid compounds. The method of the '454 Patent includes the steps of dissolving the solid compound in a suitable solvent followed by infusing precipitating liquid thereby precipitating non-aggregated particles with substantially uniform mean diameter. The particles are then separated from the solvent. The '454 Patent discourages forming particles in a crystalline state because during the precipitating procedure the crystal can dissolve and recrystallize thereby broadening the particle size distribution range. The '454 Patent encourages during the precipitating procedure to trap the particles in a metastable particle state.

United States Patent No. 5,605,785 discloses a process for forming nanoamorphous dispersions of photographically useful compounds. The process of forming nanoamorphous dispersions includes any known process of emulsification that produces a disperse phase having amorphous particulates.

SUMMARY OF THE INVENTION:

The present invention provides a method for preparing submicron sized particles of an organic compound, the solubility of which is greater in a water-miscible first solvent than in a second solvent which is aqueous. The process includes the steps of: (i) dissolving the organic compound in the water-miscible first solvent to form a solution, the first solvent being selected from the group consisting of N-methyl-2-pyrrolidinone, 2-pyrrolidone, dimethyl sulfoxide, dimethylacetamide, lactic acid, methanol, ethanol, isopropanol, 3-pentanol, n-propanol, glycerol, butylene glycol, ethylene glycol, propylene glycol, mono- and diacylated monoglycerides, dimethyl isosorbide, acetone, dimethylformamide, 1,4-

dioxane, polyethylene glycol, polyethylene glycol esters, polyethylene glycol sorbitans, polyethylene glycol monoalkyl ethers, polypropylene glycol, polypropylene alginate, PPG-10 butanediol, PPG-10 methyl glucose ether, PPG-20 methyl glucose ether, PPG-15 stearyl ether, propylene glycol dicaprylate, propylene glycol dicaprinate, propylene glycol laurate; (ii) mixing the solution with the
5 second solvent to define a pre-suspension; and (iii) adding energy to the pre-suspension to form particles having an average effective particle size of less than about 2 μm .

A method for preparing submicron sized particles of an organic compound, the solubility of which is greater in a water-miscible first solvent than in a second solvent which is aqueous, the process comprising the steps of: (i) dissolving the organic compound in the water-miscible first
10 solvent to form a solution, the first solvent being selected from the group consisting of N-methyl-2-pyrrolidinone, 2-pyrrolidone, dimethyl sulfoxide, dimethylacetamide, lactic acid, methanol, ethanol, isopropanol, 3-pentanol, n-propanol, glycerol, butylene glycol, ethylene glycol, propylene glycol, mono- and diacylated monoglycerides, dimethyl isosorbide, acetone, dimethylformamide, 1,4-dioxane, ethyl acetate, propyl acetate, polyethylene glycol, polyethylene glycol esters, polyethylene
15 glycol sorbitans, polyethylene glycol monoalkyl ethers, polypropylene glycol, polypropylene alginate, PPG-10 butanediol, PPG-10 methyl glucose ether, PPG-20 methyl glucose ether, PPG-15 stearyl ether, propylene glycol dicaprylate, propylene glycol dicaprinate, propylene glycol laurate; (ii) mixing the solution with the second solvent to define a pre-suspension wherein the organic compound is in an amorphous form, a semicrystalline form or in a supercooled liquid form as
20 determined by DSC and having an average effective particle size; and (iii) annealing the pre-suspension to form particles having essentially the same average effective particle size of the pre-suspension and in a more stable form.

The present invention further provides a method for preparing submicron sized particles of an organic compound, the solubility of which is greater in a water-miscible first solvent than in a
25 second solvent which is aqueous. The process includes the steps of: (i) dissolving the organic compound in the water-miscible first solvent to form a solution, the first solvent being selected from the group consisting of N-methyl-2-pyrrolidinone, 2-pyrrolidone, dimethyl sulfoxide, dimethylacetamide, lactic acid, methanol, ethanol, isopropanol, 3-pentanol, n-propanol, glycerol, butylene glycol, ethylene glycol, propylene glycol, mono- and diacylated monoglycerides, dimethyl
30 isosorbide, acetone, dimethylformamide, 1,4-dioxane, polyethylene glycol, polyethylene glycol esters, polyethylene glycol sorbitans, polyethylene glycol monoalkyl ethers, polypropylene glycol, polypropylene alginate, PPG-10 butanediol, PPG-10 methyl glucose ether, PPG-20 methyl glucose ether, PPG-15 stearyl ether, propylene glycol dicaprylate, propylene glycol dicaprinate, propylene glycol laurate; (ii) mixing the solution with the second solvent to define a pre-suspension of particles
35 in a friable form; and (iii) adding energy to the pre-suspension to form particles having an average

effective particle size of less than about 2 μm .

The present invention also provides a method for preparing a suspension of a pharmaceutically-active compound, the solubility of which is greater in a water-miscible first organic solvent than in a second solvent which is aqueous. The process includes the steps of: (i) dissolving a first quantity of the pharmaceutically-active compound in the water-miscible first organic solvent to form a first solution; (ii) mixing the first solution with the second solvent to precipitate the pharmaceutically-active compound; and (iii) seeding the first solution or the second solvent or the presuspension. The method further includes the step of forming a desired polymorph of the pharmaceutically active compound. In a preferred form of the invention the step of seeding includes the step of adding a seed compound to the first solution, to the second solvent and/or to the presuspension.

The present invention further provides a method for preparing a suspension of a pharmaceutically-active compound, the solubility of which is greater in a water-miscible first organic solvent than in a second solvent which is aqueous. The method includes the steps of: (i) adding a quantity of the pharmaceutically-active compound to the first organic solvent to create a supersaturated solution, (ii) aging the supersaturated solution to form detectable crystals to create a seeding mixture; and (iii) mixing the seeding mixture with the second solvent to precipitate the pharmaceutically-active compound to create a presuspension.

BRIEF DESCRIPTION OF THE DRAWINGS:

Not Applicable. The Drawings have been incorporated into the text.

DETAILED DESCRIPTION OF THE INVENTION:

The present invention is susceptible of embodiments in many different forms. Preferred embodiments of the invention are disclosed with the understanding that the present disclosure is to be considered as exemplifications of the principles of the invention and are not intended to limit the broad aspects of the invention to the embodiments illustrated.

The present invention provides methods or processes for forming particles of an organic compound having an average effective particle size suitable for parenteral administration and, in a most preferred form of the invention, is less than about 2 μm . The present invention is also suitable for providing particles of the organic compound in a form suitable for oral administration. Particles sizes for oral dosage forms can be in excess of 2 μm and typically less than about 7 μm . However, the particles can exceed 7 μm provided that the particles have sufficient bioavailability and other characteristics of an oral dosage form. Oral dosage forms include tablets, capsules, caplets, soft and hard gel capsules, or other delivery vehicle for delivering a drug by oral administration.

The processes can be separated into three general categories. Each of the categories of processes share the steps of: (1) dissolving an organic compound in a water miscible first organic solvent to create a first solution, (2) mixing the first solution with a second solvent of water to precipitate the organic compound to create a pre-suspension, and (3) adding energy to the presuspension in the form of high-shear mixing or heat to provide a stable form of the organic compound having the desired size ranges defined above.

The three categories of processes are distinguished based upon the physical properties of the organic compound as determined through x-ray diffraction studies, differential scanning calorimetry (DSC) studies or other suitable study conducted prior to the energy-addition step and after the energy-addition step. In the first process category, prior to the energy-addition step the organic compound in the presuspension takes an amorphous form, a semi-crystalline form or a supercooled liquid form and has an average effective particle size. After the energy-addition step the organic compound is in a crystalline form having an average effective particle size essentially the same as that of the presuspension (i.e., from less than about $2\mu\text{m}$).

In the second process category, prior to the energy-addition step the organic compound is in a crystalline form and has an average effective particle size. After the energy-addition step the organic compound is in a crystalline form having essentially the same average effective particle size as prior to the energy-addition step but the crystals after the energy-addition step are less likely to aggregate.

The lower tendency of the organic compound to aggregate is observed by laser dynamic light scattering and light microscopy.

In the third process category, prior to the energy-addition step the organic compound is in a crystalline form that is friable and has an average effective particle size. What is meant by the term "friable" is that the particles are fragile and are more easily broken down into smaller particles. After the energy-addition step the organic compound is in a crystalline form having an average effective particle size smaller than the crystals of the pre-suspension. By taking the steps necessary to place the organic compound in a crystalline form that is friable, the subsequent energy-addition step can be carried out more quickly and efficiently when compared to an organic compound in a less friable crystalline morphology.

The energy-addition step can be carried out in any fashion wherein the pre-suspension is exposed to cavitation, shearing or impact forces. In one preferred form of the invention, the energy-addition step is an annealing step. Annealing is defined in this invention as the process of converting matter that is thermodynamically unstable into a more stable form by single or repeated application of energy (direct heat or mechanical stress), followed by thermal relaxation. This lowering of energy may be achieved by conversion of the solid form from a less ordered to a more

ordered lattice structure. Alternatively, this stabilization may occur by a reordering of the surfactant molecules at the solid-liquid interface.

These three process categories will be discussed separately below. It should be understood, however, that the process conditions such as choice of surfactants or combination of surfactants, amount of surfactant used, temperature of reaction, rate of mixing of solutions, rate of precipitation and the like can be selected to allow for any drug to be processed under any one of the categories discussed next.

The first process category, as well as the second and third process categories, can be further divided into two subcategories, Method A, and B shown diagrammatically below.

Figure 1: Method A:





Figure 2: Method B:



An organic compound for use in the process of this invention is any organic chemical entity whose solubility decreases from one solvent to another. This organic compound might be a pharmaceutically active compound from various groups such as, but not limited to: antihyperlipidemics; antimicrobials, e.g., antibacterials such as sulfadiazine, antifungals such as itraconazole; non-steroidal anti-inflammatory drugs, e.g., indomethacin; antihypercholesteremic agents, e.g., probucol; and steroidal compounds, e.g., dexamethasone; immunosuppressants, e.g., cyclosporin A, tacrolimus, and mycophenolate mofetil. Or the organic compound might be from the group used as adjuvants or excipients in pharmaceutical preparations and cosmetics, such as, but not limited to, preservatives, e.g., propylparaben.

The first solvent according to the present invention is a solvent or mixture of solvents in which the organic compound of interest is relatively soluble and which is miscible with the second solvent. Examples of such solvents include, but are not limited to: polyvinylpyrrolidone, N-methyl-2-pyrrolidinone (also called N-methyl-2-pyrrolidone), 2-pyrrolidone, dimethyl sulfoxide, dimethylacetamide, lactic acid, methanol, ethanol, isopropanol, 3-pentanol, n-propanol, glycerol, butylene glycol (butanediol), ethylene glycol, propylene glycol, mono- and diacylated monoglycerides (such as glyceryl caprylate), dimethyl isosorbide, acetone, dimethylformamide, 1,4-dioxane, polyethylene glycol (for example, PEG-4, PEG-8, PEG-9, PEG-12, PEG-14, PEG-16, PEG-120, PEG-75, PEG-150, polyethylene glycol esters (examples such as PEG-4 dilaurate, PEG-20 dilaurate, PEG-6 isostearate, PEG-8 palmitostearate, PEG-150 palmitostearate), polyethylene glycol sorbitans (such as PEG-20 sorbitan isostearate), polyethylene glycol monoalkyl ethers (examples such as PEG-3 dimethyl ether, PEG-4 dimethyl ether), polypropylene glycol (PPG), polypropylene alginate, PPG-10 butanediol, PPG-10 methyl glucose ether, PPG-20 methyl glucose ether, PPG-15 stearyl ether, propylene glycol dicaprylate/dicaprate, propylene glycol laurate.

Method A

In Method A (see Figure 1), the organic compound ("drug") is first dissolved in the first solvent to create a first solution. The organic compound can be added from about 0.1% (w/v) to about 50% (w/v) depending on the solubility of the organic compound in the first solvent. Heating of the concentrate from about 30°C to about 100°C may be necessary to ensure total dissolution of the compound in the first solvent.

A second aqueous solution is provided with one or more optional surface modifiers such as an anionic surfactant, a cationic surfactant, a nonionic surfactant or a biological surface active molecule added thereto. Suitable anionic surfactants include but are not limited to potassium laurate, sodium lauryl sulfate, sodium dodecylsulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, phosphatidyl choline, phosphatidyl glycerol, phosphatidyl inosine, phosphatidylserine, phosphatidic acid and their salts, glyceryl esters, sodium

carboxymethylcellulose, cholic acid and other bile acids (e.g., cholic acid, deoxycholic acid, glycocholic acid, taurocholic acid, glycodeoxycholic acid) and salts thereof (e.g., sodium deoxycholate, etc.). Suitable cationic surfactants include but are not limited to quaternary ammonium compounds, such as benzalkonium chloride, cetyltrimethylammonium bromide, lauryldimethylbenzylammonium chloride, acyl carnitine hydrochlorides, or alkyl pyridinium halides.

As anionic surfactants, phospholipids may be used. Suitable phospholipids include, for example phosphatidylcholine, phosphatidylethanolamine, phosphatidylserine, phosphatidylinositol, phosphatidylglycerol, phosphatidic acid, lysophospholipids, egg or soybean phospholipid or a combination thereof. The phospholipid may be salted or desalted, hydrogenated or partially hydrogenated or natural semisynthetic or synthetic.

Suitable nonionic surfactants include: polyoxyethylene fatty alcohol ethers (Macrogol and Brij), polyoxyethylene sorbitan fatty acid esters (Polysorbates), polyoxyethylene fatty acid esters (Myrj), sorbitan esters (Span), glycerol monostearate, polyethylene glycols, polypropylene glycols, cetyl alcohol, cetostearyl alcohol, stearyl alcohol, aryl alkyl polyether alcohols, polyoxyethylene-polyoxypropylene copolymers (poloxomers), polaxamines, methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline cellulose, polysaccharides including starch and starch derivatives such as hydroxyethylstarch (HES), polyvinyl alcohol, and polyvinylpyrrolidone. In a preferred form of the invention, the nonionic surfactant is a polyoxyethylene and polyoxypropylene copolymer and preferably a block copolymer of propylene glycol and ethylene glycol. Such polymers are sold under the tradename POLOXAMER also sometimes referred to as PLURONIC®, and sold by several suppliers including Spectrum Chemical and Ruger. Among polyoxyethylene fatty acid esters is included those having short alkyl chains. One example of such a surfactant is SOLUTOL® HS 15, polyethylene-660-hydroxystearate, manufactured by BASF Aktiengesellschaft.

Surface active biological molecules include such molecules as albumin, casein, heparin, hirudin or other appropriate proteins.

It may also be desirable to add a pH adjusting agent to the second solution such as sodium hydroxide, hydrochloric acid, tris buffer or citrate, acetate, lactate, meglumine, or the like. The second solution should have a pH within the range of from about 3 to about 11.

For oral dosage forms one or more of the following excipients may be utilized: gelatin, casein, lecithin (phosphatides), gum acacia, cholesterol, tragacanth, stearic acid, benzalkonium chloride, calcium stearate, glyceryl monostearate, cetostearyl alcohol, cetomacrogol emulsifying wax, sorbitan esters, polyoxyethylene alkyl ethers, e.g., macrogol ethers such as cetomacrogol 1000, polyoxyethylene castor oil derivatives, polyoxyethylene sorbitan fatty acid esters, e.g., the commercially available Tweens.TM., polyethylene glycols, polyoxyethylene stearates, colloidol

silicon dioxide, phosphates, sodium dodecylsulfate, carboxymethylcellulose calcium, carboxymethylcellulose sodium, methylcellulose, hydroxyethylcellulose, hydroxypropylcellulose, hydroxypropylmethylcellulose phthalate, noncrystalline cellulose, magnesium aluminum silicate, triethanolamine, polyvinyl alcohol (PVA), and polyvinylpyrrolidone (PVP). Most of these excipients
5 are described in detail in the Handbook of Pharmaceutical Excipients, published jointly by the American Pharmaceutical Association and The Pharmaceutical Society of Great Britain, the Pharmaceutical Press, 1986. The surface modifiers are commercially available and/or can be prepared by techniques known in the art. Two or more surface modifiers can be used in combination.

10 In a preferred form of the invention, the method for preparing submicron sized particles of an organic compound includes the steps of adding the first solution to the second solution. The addition rate is dependent on the batch size, and precipitation kinetics for the organic compound. Typically, for a small-scale laboratory process (preparation of 1 liter), the addition rate is from about 0.05 cc per minute to about 10 cc per minute. During the addition, the solutions should be under
15 constant agitation. It has been observed using light microscopy that amorphous particles, semi-crystalline solids, or a supercooled liquid are formed to create a pre-suspension. The method further includes the step of subjecting the pre-suspension to an annealing step to convert the amorphous particles, supercooled liquid or semicrystalline solid to a crystalline more stable solid state. The resulting particles will have an average effective particles size as measured by dynamic light
20 scattering methods (e.g., photocorrelation spectroscopy, laser diffraction, low-angle laser light scattering (LALLS), medium-angle laser light scattering (MALLS), light obscuration methods (Coulter method, for example), rheology, or microscopy (light or electron) within the ranges set forth above).

The energy-addition step involves adding energy through sonication, homogenization,
25 counter current flow homogenization, microfluidization, or other methods of providing impact, shear or cavitation forces. The sample may be cooled or heated during this stage. In one preferred form of the invention the annealing step is effected by a piston gap homogenizer such as the one sold by Avestin Inc. under the product designation EmulsiFlex-C160. In another preferred form of the invention, the annealing may be accomplished by ultrasonication using an ultrasonic processor such
30 as the Vibra-Cell Ultrasonic Processor (600W), manufactured by Sonics and Materials, Inc. In yet another preferred form of the invention, the annealing may be accomplished by use of an emulsification apparatus as described in U.S. Patent No. 5,720,551 which is incorporated herein by reference and made a part hereof.

Depending upon the rate of annealing, it may be desirable to adjust the temperature of the
35 processed sample to within the range of from approximately -30°C to 30°C. Alternatively, in order

to effect a desired phase change in the processed solid, it may also be necessary to heat the pre-suspension to a temperature within the range of from about 30°C to about 100°C during the annealing step.

Method B

5 Method B differs from Method A in the following respects. The first difference is a surfactant or combination of surfactants is added to the first solution. The surfactants may be selected from the groups of anionic, nonionic and cationic surfactants set forth above.

Comparative Example of Method A and Method B and USPN 5,780,062

10 United States Patent No. 5,780,062 discloses a process for preparing small particles of an organic compound by first dissolving the compound in a suitable water-miscible first solvent. A second solution is prepared by dissolving a polymer and an amphiphile in aqueous solution. The first solution is then added to the second solution to form a precipitate that consists of the organic compound and a polymer-amphiphile complex. The '062 Patent does not disclose utilizing the
15 energy-addition step of this invention in Methods A and B. Lack of stability is typically evidenced by rapid aggregation and particle growth. In some instances, amorphous particles recrystallize as large crystals. Adding energy to the pre-suspension in the manner disclosed above typically affords particles that show decreased rates of particle aggregation and growth, as well as the absence of recrystallization upon product storage.

20 Methods A and B are further distinguished from the process of the '062 patent by the absence of a step of forming a polymer-amphiphile complex prior to precipitation. In Method A, such a complex cannot be formed as no polymer is added to the diluent (aqueous) phase. In Method B, the surfactant, which may also act as an amphiphile, or polymer, is dissolved with the organic compound in the first solvent. This precludes the formation of any amphiphile-polymer complexes
25 prior to precipitation. In the '062 Patent, successful precipitation of small particles relies upon the formation of an amphiphile-polymer complex prior to precipitation. The '062 Patent discloses the amphiphile-polymer complex forms aggregates in the aqueous second solution. The '062 Patent explains the hydrophobic organic compound interacts with the amphiphile-polymer complex, thereby reducing solubility of these aggregates and causing precipitation. In the present invention it
30 has been demonstrated that the inclusion of the surfactant or polymer in the first solvent (Method B) leads, upon subsequent addition to second solvent, to formation of a more uniform, finer particulate than is afforded by the process outlined by the '062 Patent.

 To this end, two formulations were prepared and analyzed. Each of the formulations have two solutions, a concentrate and an aqueous diluent, which are mixed together and then sonicated.
35 The concentrate in each formulation has an organic compound (itraconazole), a water miscible

solvent (N-methyl-2-pyrrolidinone or NMP) and possibly a polymer (poloxamer 188). The aqueous diluent has water, a tris buffer and possibly a polymer (poloxamer 188) and/or a surfactant (sodium deoxycholate). The average particle diameter of the organic particle is measured prior to sonication and after sonication.

5 The first formulation A has as the concentrate itraconazole and NMP. The aqueous diluent includes water, poloxamer 188, tris buffer and sodium deoxycholate. Thus the aqueous diluent includes a polymer (poloxamer 188), and an amphiphile (sodium deoxycholate), which may form a polymer/amphiphile complex, and, therefore, is in accordance with the disclosure of the '062 Patent. (However, again the '062 Patent does not disclose an energy addition step.)

10 The second formulation B has as the concentrate itraconazole, NMP and poloxamer 188. The aqueous diluent includes water, tris buffer and sodium deoxycholate. This formulation is made in accordance with the present invention. Since the aqueous diluent does not contain a combination of a polymer (poloxamer) and an amphiphile (sodium deoxycholate), a polymer/amphiphile complex cannot form prior to the mixing step.

15 Table 1 shows the average particle diameters measured by laser diffraction on three replicate suspension preparations. An initial size determination was made, after which the sample was sonicated for 1 minute. The size determination was then repeated. The large size reduction upon sonication of Method A was indicative of particle aggregation.

20 Table 1:

Method	Concentrate	Aqueous Diluent	Average particle diameter (microns)	After sonication (1 minute)
A	itraconazole (18%), N-methyl-2-pyrrolidinone (6 mL)	poloxamer 188 (2.3%), sodium deoxycholate (0.3%) tris buffer (5 mM, pH 8) water (qs to 94 mL)	18.7 10.7 12.1	2.36 2.46 1.93
B	itraconazole (18%) poloxamer 188 (37%) N-methyl-2-pyrrolidinone (6 mL)	sodium deoxycholate (0.3%) tris buffer (5 mM, pH 8) water (qs to 94 mL)	0.194 0.178 0.181	0.198 0.179 0.177

A drug suspension resulting from application of the processes described in this invention may be administered directly as an injectable solution, provided Water for Injection is used in formulation and an appropriate means for solution sterilization is applied. Sterilization may be accomplished by separate sterilization of the drug concentrate (drug, solvent, and optional surfactant) and the diluent medium (water, and optional buffers and surfactants) prior to mixing to form the pre-suspension. Sterilization methods would include pre-filtration first through a 3.0

micron filter followed by filtration through a 0.45-micron particle filter, followed by steam or heat sterilization or sterile filtration through two redundant 0.2-micron membrane filters.

Optionally, a solvent-free suspension may be produced by solvent removal after precipitation. This can be accomplished by centrifugation, dialysis, diafiltration, force-field
5 fractionation, high-pressure filtration or other separation techniques well known in the art. Complete removal of N-methyl-2-pyrrolidinone was typically carried out by one to three successive centrifugation runs; after each centrifugation (18,000 rpm for 30 minutes) the supernatant was decanted and discarded. A fresh volume of the suspension vehicle without the organic solvent was added to the remaining solids and the mixture was dispersed by homogenization. It will be
10 recognized by others skilled in the art that other high-shear mixing techniques could be applied in this reconstitution step.

Furthermore, any undesired excipients such as surfactants may be replaced by a more desirable excipient by use of the separation methods described in the above paragraph. The solvent and first excipient may be discarded with the supernatant after centrifugation or filtration. A fresh
15 volume of the suspension vehicle without the solvent and without the first excipient may then be added. Alternatively, a new surfactant may be added. For example, a suspension consisting of drug, N-methyl-2-pyrrolidinone (solvent), poloxamer 188 (first excipient), sodium deoxycholate, glycerol and water may be replaced with phospholipids (new surfactant), glycerol and water after centrifugation and removal of the supernatant.

20 I. First Process Category

The methods of the first process category generally include the step of dissolving the organic compound in a water miscible first solvent followed by the step of mixing this solution with an aqueous solution to form a presuspension wherein the organic compound is in an amorphous form, a
25 semicrystalline form or in a supercooled liquid form as determined by x-ray diffraction studies, DSC, light microscopy or other analytical techniques and has an average effective particle size within one of the effective particle size ranges set forth above. The mixing step is followed by an energy-addition step and, in a preferred form of the invention an annealing step.

30 II. Second Process Category

The methods of the second processes category include essentially the same steps as in the steps of the first processes category but differ in the following respect. An x-ray diffraction, DSC or other suitable analytical techniques of the presuspension shows the organic compound in a crystalline form and having an average effective particle size. The organic compound after the
35 energy-addition step has essentially the same average effective particle size as prior to the energy-

addition step but has less of a tendency to aggregate into larger particles when compared to that of the particles of the presuspension. Without being bound to a theory, it is believed the differences in the particle stability may be due to a reordering of the surfactant molecules at the solid-liquid interface.

5

III. Third Process Category

The methods of the third category modify the first two steps of those of the first and second processes categories to ensure the organic compound in the presuspension is in a friable form having an average effective particle size (e.g., such as slender needles and thin plates). Friable particles can be formed by selecting suitable solvents, surfactants or combination of surfactants, the temperature of the individual solutions, the rate of mixing and rate of precipitation and the like. Friability may also be enhanced by the introduction of lattice defects (e.g., cleavage planes) during the steps of mixing the first solution with the aqueous solution. This would arise by rapid crystallization such as that afforded in the precipitation step. In the energy-addition step these friable crystals are converted to crystals that are kinetically stabilized and having an average effective particle size smaller than those of the presuspension. Kinetically stabilized means particles have a reduced tendency to aggregate when compared to particles that are not kinetically stabilized. In such instance the energy-addition step results in a breaking up of the friable particles. By ensuring the particles of the presuspension are in a friable state, the organic compound can more easily and more quickly be prepared into a particle within the desired size ranges when compared to processing an organic compound where the steps have not been taken to render it in a friable form.

Polymorph Control

The present invention further provides additional steps for controlling the crystal structure of the pharmaceutically-active compound to ultimately produce a suspension of the compound in the desired size range and a desired crystal structure. What is meant by the term "crystal structure" is the arrangement of the atoms within the unit cell of the crystal. Pharmaceutically-active compounds that can be crystallized into different crystal structures are said to be polymorphic. Identification of polymorphs is important step in drug formulation since different polymorphs of the same drug can show differences in solubility, therapeutic activity, bioavailability, and suspension stability. Accordingly, it is important to control the polymorphic form of the compound for ensuring product purity and batch-to-batch reproducibility.

The steps to control the polymorphic form of the compound includes seeding the first solution, the second solvent or the presuspension to ensure the formation of the desired polymorph. Seeding includes using a seed compound or adding energy. In a preferred form of the invention the seed compound is the pharmaceutically-active compound in the desired polymorphic form.

Alternatively, the seed compound can also be an inert impurity or an organic compound with a structure similar to that of the desired polymorph such as a bile salt.

The seed compound can be precipitated from the first solution. This method includes the steps of adding the pharmaceutically-active compound in sufficient quantity to exceed the solubility of the pharmaceutically-active compound in the first solvent to create a supersaturated solution. The supersaturated solution is treated to precipitate the pharmaceutically-active compound in the desired polymorphic form. Treating the supersaturated solution includes aging the solution for a time period until the formation of a crystal or crystals is observed to create a seeding mixture. It is also possible to add energy to the supersaturated solution to cause the pharmaceutically-active compound to precipitate out of the solution in the desired polymorph. The energy can be added in a variety of ways including the energy addition steps described above. Further energy can be added by heating or exposing the presuspension to electromagnetic energy, particle beam, or electron beam sources. The electromagnetic energy includes using a laser beam, dynamic electromagnetic energy, or other radiation sources. It is further contemplated utilizing ultrasound, static electric field and a static magnetic field as the energy addition source.

In a preferred form of the invention, the method for producing seed crystals from an aged supersaturated solution includes the steps of: (i) adding a quantity of the pharmaceutically-active compound to the first organic solvent to create a supersaturated solution; (ii) aging the supersaturated solution to form detectable crystals to create a seeding mixture; and (iii) mixing the seeding mixture with the second solvent to precipitate the pharmaceutically-active compound to create a presuspension. The presuspension can then be further processed as described in detail above to provide an aqueous suspension of the pharmaceutically-active compound in the desired polymorph and in the desired size range.

Seeding can also be accomplished by adding energy to the first solution, the second solvent or the presuspension provided that the exposed liquid or liquids contain the pharmaceutically active compound or a seed material. The energy can be added in the same fashion as described above for the supersaturated solution.

Accordingly, the present invention provides a composition of matter of a pharmaceutically active compound in a desired polymorphic form essentially free of the unspecified polymorph or polymorphs. One such example is set forth in example 16 below where seeding during microprecipitation provides a polymorph of itraconazole essentially free of the polymorph of the raw material. It is contemplated the methods of this invention can apply used to selectively produce a desired polymorph for numerous pharmaceutically active compounds.

Examples

Examples of Process Category 1

Example 1: Preparation of itraconazole suspension by use of Process Category 1, Method A with homogenization.

5 To a 3-L flask add 1680 mL of Water for Injection. Heat liquid to 60-65°C, and then slowly add 44 grams of Pluronic F-68 (poloxamer 188), and 12 grams of sodium deoxycholate, stirring after each addition to dissolve the solids. After addition of solids is complete, stir for another 15 minutes at 60-65°C to ensure complete dissolution. Prepare a 50 mM tris (tromethamine) buffer by dissolving 6.06 grams of tris in 800 mL of Water for Injection. Titrate this solution to pH 8.0 with
10 0.1 M hydrochloric acid. Dilute the resulting solution to 1 liter with additional Water for Injection. Add 200 mL of the tris buffer to the poloxamer/deoxycholate solution. Stir thoroughly to mix solutions.


In a 150-mL beaker add 20 grams of itraconazole and 120 mL of N-methyl-2-pyrrolidinone. Heat mixture to 50-60°C, and stir to dissolve solids. After total dissolution is visually apparent, stir
15 another 15 minutes to ensure complete dissolution. Cool itraconazole-NMP solution to room temperature.

Charge a syringe pump (two 60-mL glass syringes) with the 120-mL of itraconazole solution prepared previously. Meanwhile pour all of the surfactant solution into a homogenizer hopper which has been cooled to 0-5°C (this may either be accomplished by use of a jacketed hopper through
20 which refrigerant is circulated, or by surrounding the hopper with ice). Position a mechanical stirrer into the surfactant solution so that the blades are fully immersed. Using the syringe pump, slowly (1-3 mL/min) add all of the itraconazole solution to the stirred, cooled surfactant solution. A stirring rate of at least 700 rpm is recommended. An aliquot of the resulting suspension (Suspension A) is analyzed by light microscopy (Hoffman Modulation Contrast) and by laser diffraction (Horiba).
25 Suspension A is observed by light microscopy to consist of roughly spherical amorphous particles (under 1 micron), either bound to each other in aggregates or freely moving by Brownian motion. See Figure 3. Dynamic light scattering measurements typically afford a bimodal distribution pattern signifying the presence of aggregates (10-100 microns in size) and the presence of single amorphous particles ranging 200-700 nm in median particle diameter.

30 The suspension is immediately homogenized (at 10,000 to 30,000 psi) for 10-30 minutes. At the end of homogenization, the temperature of the suspension in the hopper does not exceed 75°C. The homogenized suspension is collected in 500-mL bottles, which are cooled immediately in the refrigerator (2-8°C). This suspension (Suspension B) is analyzed by light microscopy and is found to consist of small elongated plates with a length of 0.5 to 2 microns and a width in the 0.2-1 micron
35 range. See Figure 4. Dynamic light scattering measurements typically indicate a median diameter


of 200-700 nm.

Figure 3: Amorphous particles prior to homogenization (Example 1).



5

Figure 4: Particles after annealing by homogenization.



Stability of Suspension A ("Pre-suspension") (Example 1)

10

During microscopic examination of the aliquot of Suspension A, crystallization of the amorphous solid was directly observed. Suspension A was stored at 2-8 °C for 12 hours and examined by light microscopy. Gross visual inspection of the sample revealed severe flocculation,

with some of the contents settling to the bottom of the container. Microscopic examination indicated the presence of large, elongated, plate-like crystals over 10 microns in length.

Stability of Suspension B

As opposed to the instability of Suspension A, Suspension B was stable at 2-8°C for the duration of the preliminary stability study (1 month). Microscopy on the aged sample clearly demonstrated that no significant change in the morphology or size of the particles had occurred. This was confirmed by light scattering measurement.

Example 2: Preparation of itraconazole suspension by use of Process Category 1, Method A with ultrasonication.

To a 500-mL stainless steel vessel add 252 mL of Water for Injection. Heat liquid to 60-65°C, and then slowly add 6.6 grams of Pluronic F-68 (poloxamer 188), and 0.9 grams of sodium deoxycholate, stirring after each addition to dissolve the solids. After addition of solids is complete, stir for another 15 minutes at 60-65°C to ensure complete dissolution. Prepare a 50 mM tris (tromethamine) buffer by dissolving 6.06 grams of tris in 800 mL of Water for Injection. Titrate this solution to pH 8.0 with 0.1 M hydrochloric acid. Dilute the resulting solution to 1 liter with additional Water for Injection. Add 30 mL of the tris buffer to the poloxamer/deoxycholate solution. Stir thoroughly to mix solutions.

In a 30-mL container add 3 grams of itraconazole and 18 mL of N-methyl-2-pyrrolidinone. Heat mixture to 50-60°C, and stir to dissolve solids. After total dissolution is visually apparent, stir another 15 minutes to ensure complete dissolution. Cool itraconazole-NMP solution to room temperature.

Charge a syringe pump with 18-mL of itraconazole solution prepared in a previous step. Position a mechanical stirrer into the surfactant solution so that the blades are fully immersed. Cool the container to 0-5°C by immersion in an ice bath. Using the syringe pump, slowly (1-3 mL/min) add all of the itraconazole solution to the stirred, cooled surfactant solution. A stirring rate of at least 700 rpm is recommended. Immerse an ultrasonicator horn in the resulting suspension so that the probe is approximately 1 cm above the bottom of the stainless steel vessel. Sonicate (10,000 to 25,000 Hz, at least 400W) for 15 to 20 minute in 5-minute intervals. After the first 5-minute sonication, remove the ice bath and proceed with further sonication. At the end of ultrasonication, the temperature of the suspension in the vessel does not exceed 75°C.

The suspension is collected in a 500-mL Type I glass bottle, which is cooled immediately in the refrigerator (2-8°C). Characteristics of particle morphology of the suspension before and after sonication were very similar to that seen in Method A before and after homogenization (see Example 1).

Example 3: Preparation of itraconazole suspension by use of Process Category 1, Method B with homogenization.

Prepare a 50 mM tris (tromethamine) buffer by dissolving 6.06 grams of tris in 800 mL of Water for Injection. Titrate this solution to pH 8.0 with 0.1 M hydrochloric acid. Dilute the resulting solution to 1 liter with additional Water for Injection. To a 3-L flask add 1680 mL of Water for Injection. Add 200 mL of the tris buffer to the 1680 mL of water. Stir thoroughly to mix solutions.

In a 150-mL beaker add 44 grams of Pluronic F-68 (poloxamer 188) and 12 grams of sodium deoxycholate to 120 mL of N-methyl-2-pyrrolidinone. Heat the mixture to 50-60°C, and stir to dissolve solids. After total dissolution is visually apparent, stir another 15 minutes to ensure complete dissolution. To this solution, add 20 grams of itraconazole, and stir until totally dissolved. Cool the itraconazole-surfactant-NMP solution to room temperature.

Charge a syringe pump (two 60-mL glass syringes) with the 120-mL of the concentrated itraconazole solution prepared previously. Meanwhile pour the diluted tris buffer solution prepared above into a homogenizer hopper which has been cooled to 0-5°C (this may either be accomplished by use of a jacketed hopper through which refrigerant is circulated, or by surrounding the hopper with ice). Position a mechanical stirrer into the buffer solution so that the blades are fully immersed.

Using the syringe pump, slowly (1-3 mL/min) add all of the itraconazole-surfactant concentrate to the stirred, cooled buffer solution. A stirring rate of at least 700 rpm is recommended. The resulting cooled suspension is immediately homogenized (at 10,000 to 30,000 psi) for 10-30 minutes. At the end of homogenization, the temperature of the suspension in the hopper does not exceed 75°C.

The homogenized suspension is collected in 500-mL bottles, which are cooled immediately in the refrigerator (2-8°C). Characteristics of particle morphology of the suspension before and after homogenization were very similar to that seen in Example 1, except that in process category 1 B, the pre-homogenized material tended to form fewer and smaller aggregates which resulted in a much smaller overall particle size as measured by laser diffraction. After homogenization, dynamic light scattering results were typically identical to those presented in Example 1.

Example 4: Preparation of itraconazole suspension by use of Process Category 1, Method B with ultrasonication.

To a 500-mL flask add 252 mL of Water for Injection. Prepare a 50 mM tris (tromethamine) buffer by dissolving 6.06 grams of tris in 800 mL of Water for Injection. Titrate this solution to pH 8.0 with 0.1 M hydrochloric acid. Dilute the resulting solution to 1 liter with additional Water for Injection. Add 30 mL of the tris buffer to the water. Stir thoroughly to mix solutions.

In a 30-mL beaker add 6.6 grams of Pluronic F-68 (poloxamer 188) and 0.9 grams of sodium deoxycholate to 18 mL of N-methyl-2-pyrrolidinone. Heat the mixture to 50-60°C, and stir to dissolve solids. After total dissolution is visually apparent, stir another 15 minutes to ensure complete dissolution. To this solution, add 3.0 grams of itraconazole, and stir until totally dissolved.

5 Cool the itraconazole-surfactant-NMP solution to room temperature.

Charge a syringe pump (one 30-mL glass syringe with the 18-mL of the concentrated itraconazole solution prepared previously. Position a mechanical stirrer into the buffer solution so that the blades are fully immersed. Cool the container to 0-5°C by immersion in an ice bath. Using the syringe pump, slowly (1-3 mL/min) add all of the itraconazole-surfactant concentrate to the stirred, cooled buffer solution. A stirring rate of at least 700 rpm is recommended. The resulting cooled suspension is immediately sonicated (10,000 to 25,000 Hz, at least 400 W) for 15-20 minutes, in 5-minute intervals. After the first 5-minute sonication, remove the ice bath and proceed with further sonication. At the end of ultrasonication, the temperature of the suspension in the hopper does not exceed 75°C.

15 The resultant suspension is collected in a 500-mL bottle, which is cooled immediately in the refrigerator (2-8°C). Characteristics of particle morphology of the suspension before and after sonication were very similar to that seen in Example 1, except that in Process Category 1, Method B, the pre-sonicated material tended to form fewer and smaller aggregates which resulted in a much smaller overall particle size as measured by laser diffraction. After ultrasonication, dynamic light scattering results were typically identical to those presented in Example 1.

B. Examples of Process Category 2


Example 5: Preparation of itraconazole suspension (1%) with 0.75% Solutol® HR (PEG-660 12-hydroxystearate) Process Category 2, Method B.

25 Solutol (2.25 g) and itraconazole (3.0 g) were weighed into a beaker and 36 mL of filtered N-methyl-2-pyrrolidinone (NMP) was added. This mixture was stirred under low heat (up to 40°C) for approximately 15 minutes until the solution ingredients were dissolved. The solution was cooled to room temperature and was filtered through a 0.2-micron filter under vacuum. Two 60-mL syringes were filled with the filtered drug concentrate and were placed in a syringe pump. The pump was set to deliver approximately 1 mL/min of concentrate to a rapidly stirred (400 rpm) aqueous buffer solution. The buffer solution consisted of 22 g/L of glycerol in 5 mM tris buffer. Throughout concentrate addition, the buffer solution was kept in an ice bath at 2-3°C. At the end of the precipitation, after complete addition of concentrate to the buffer solution, about 100 mL of the suspension was centrifuged for 1 hour, the supernatant was discarded. The precipitate was resuspended in a 20% NMP solution in water, and again centrifuged for 1 hour. The material was

dried overnight in a vacuum oven at 25°C. The dried material was transferred to a vial and analyzed by X-ray diffractometry using chromium radiation (see Figure 5).

Another 100 mL-aliquot of the microprecipitated suspension was sonicated for 30 minutes at 20,000 Hz, 80% full amplitude (full amplitude = 600 W). The sonicated sample was homogenized in 3 equal aliquots each for 45 minutes (Avestin C5, 2-5°C, 15,000-20,000 psi). The combined fractions were centrifuged for about 3 hours, the supernatant removed, and the precipitate resuspended in 20% NMP. The resuspended mixture was centrifuged again (15,000 rpm at 5°C). The supernatant was decanted off and the precipitate was vacuum dried overnight at 25°C. The precipitate was submitted for analysis by X-ray diffractometry (see Figure 5). As seen in Figure 5, the X-ray diffraction patterns of processed samples, before and after homogenization, are essentially identical, yet show a significantly different pattern as compared with the starting raw material. The unhomogenized suspension is unstable and agglomerates upon storage at room temperature. The stabilization that occurs as a result of homogenization is believed to arise from rearrangement of surfactant on the surface of the particle. This rearrangement should result in a lower propensity for particle aggregation.

Figure 5: X-Ray diffractogram of microprecipitated itraconazole with polyethylene glycol-660 12-hydroxystearate before and after homogenization (Example 5).



C. Examples of Process Category

Example 6: Preparation of carbamazepine suspension by use of Process Category 3, Method A with homogenization.

2.08 g of carbamazepine was dissolved into 10 mL of NMP. 1.0 mL of this concentrate was subsequently dripped at 0.1 mL/min into 20 mL of a stirred solution of 1.2% lecithin and 2.25% glycerin. The temperature of the lecithin system was held at 2-5°C during the entire addition. The predispersion was next homogenized cold (5-15°C) for 35 minutes at 15,000 psi. The pressure was increased to 23,000 psi and the homogenization was continued for another 20 minutes. The particles produced by the process had a mean diameter of 0.881 μm with 99% of the particles being less than 2.44 μm .

Example 7: Preparation of 1% carbamazepine suspension with 0.125% Solutol[®] by use of Process Category 3, Method B with homogenization.

A drug concentrate of 20% carbamazepine and 5% glycodeoxycholic acid (Sigma Chemical Co.) in N-methyl-2-pyrrolidinone was prepared. The microprecipitation step involved adding the drug concentrate to the receiving solution (distilled water) at a rate of 0.1 mL/min. The receiving solution was stirred and maintained at approximately 5° C during precipitation. After precipitation, the final ingredient concentrations were 1% carbamazepine and 0.125% Solutol[®]. The drug crystals were examined under a light microscope using positive phase contrast (400X). The precipitate consisted of fine needles approximately 2 microns in diameter and ranging from 50 – 150 microns in length.

Homogenization (Avestin C-50 piston-gap homogenizer) at approximately 20,000 psi for approximately 15 minutes results in small particles, less than 1 micron in size and largely unaggregated. Laser diffraction analysis (Horiba) of the homogenized material showed that the particles had a mean size of 0.4 micron with 99% of the particles less than 0.8 micron. Low energy sonication, suitable for breaking agglomerated particles, but not with sufficient energy to cause a cominution of individual particles, of the sample before Horiba analysis had no effect on the results (numbers were the same with and without sonication). This result was consistent with the absence of particle agglomeration.

Samples prepared by the above process were centrifuged and the supernatant solutions replaced with a replacement solution consisting of 0.125% Solutol[®]. After centrifugation and supernatant replacement, the suspension ingredient concentrations were 1% carbamazepine and 0.125% Solutol[®]. The samples were re-homogenized by piston-gap homogenizer and stored at 5° C. After 4 weeks storage, the suspension had a mean particle size of 0.751 with 99% less than 1.729. Numbers reported are from Horiba analysis on unsonicated samples.

Example 8: Preparation of 1% carbamazepine suspension with 0.06% sodium glycodeoxycholate and 0.06% poloxamer 188 by use of Process Category 3, Method B with homogenization.

5 A drug concentrate comprising 20% carbamazepine and 5% glycodeoxycholate in N-methyl-2-pyrrolidinone was prepared. The microprecipitation step involved adding the drug concentrate to the receiving solution (distilled water) at a rate of 0.1 mL/min. Thus, this and the following examples demonstrate that adding a surfactant or other excipient to the aqueous precipitating solution in Methods A and B above is optional. The receiving solution was stirred and maintained at approximately 5° C during precipitation. After precipitation, the final ingredient concentrations
10 were 1% carbamazepine and 0.125% Solutol®. The drug crystals were examined under a light microscope using positive phase contrast (400X). The precipitate consisted of fine needles approximately 2 microns in diameter and ranging from 50 – 150 microns in length. Comparison of the precipitate with the raw material before precipitation reveals that the precipitation step in the presence of surface modifier (glycodeoxycholic acid) results in very slender crystals that are much
15 thinner than the starting raw material (see Figure 6).

Homogenization (Avestin C-50 piston-gap homogenizer) at approximately 20,000 psi for approximately 15 minutes results in small particles, less than 1 micron in size and largely unaggregated. See Figure 7. Laser diffraction analysis (Horiba) of the homogenized material showed that the particles had a mean size of 0.4 micron with 99% of the particles less than 0.8
20 micron. Sonication of the sample before Horiba analysis had no effect on the results (numbers were the same with and without sonication). This result was consistent with the absence of particle agglomeration.

Samples prepared by the above process were centrifuged and the supernatant solutions replaced with a replacement solution consisting of 0.06% glycodeoxycholic acid (Sigma Chemical
25 Co.) and 0.06% Poloxamer 188. The samples were re-homogenized by piston-gap homogenizer and stored at 5° C. After 2 weeks storage, the suspension had a mean particle size of 0.531 micron with 99% less than 1.14 micron. Numbers reported are from Horiba analysis on unsonicated samples.

Figure 6: Carbamazepine crystals before homogenization (Example 6).





Figure 7: Carbamazepine microparticulate after homogenization (Avestin C-50)



(Example 6).

5

Mathematical Analysis (Example 8) of force required to break precipitated particles as compared to force required to break particles of the starting raw material (carbamazepine):

The width of the largest crystals seen in the carbamazepine raw material (Figure 6, picture on left) are roughly 10-fold greater than the width of crystals in the microprecipitated material (Figure 6, picture on right). On the assumption that the ratio of crystal thickness (1:10) is proportional to the ratio of crystal width (1:10), then the moment of force required to cleave the larger crystal in the raw material should be approximately 1,000-times greater than the force needed to break the microprecipitated material, since:

$$e_L = 6PL/(Ewx^2)$$

Eq. 1

15 where,

e_L = longitudinal strain required to break the crystal ("yield value")

P = load on beam

L = distance from load to fulcrum

E = elasticity modulus

w = width of crystal

x = thickness of crystal

Let us assume that L and E are the same for the raw material and the precipitated material. Additionally, let us assume that $w/w_0 = x/x_0 = 10$. Then,

$(e_L)_0 = 6P_0L/(Ew_0x_0^2)$, where the '0' subscripts refer to raw material

$e_L = 6PL/(Ewx^2)$, for the microprecipitate

Equating $(e_L)_0$ and e_L ,

$$6PL/(Ewx^2) = 6P_0L/(Ew_0x_0^2)$$

After simplification,

$$P = P_0 (w/w_0) (x/x_0)^2 = P_0 (0.1) (0.1)^2 = 0.001 P_0$$

Thus, the yield force, P, required to break the microprecipitated solid is one-thousandth the required force necessary to break the starting crystalline solid. If, because of rapid precipitation, lattice defects or amorphous properties are introduced, then the modulus (E) should decrease, making the microprecipitate even easier to cleave.

Example 9: Preparation of 1.6% (w/v) prednisolone suspension with 0.05% sodium deoxycholate and 3% N-methyl-2-pyrrolidinone Process Category 3, Method B


A schematic of the overall manufacturing process is presented in Figure 8. A concentrated solution of prednisolone and sodium deoxycholate was prepared. Prednisolone (32g) and sodium deoxycholate (1g) were added to a sufficient volume of 1-methyl 2-pyrrolidinone (NMP) to produce a final volume of 60 mL. The resulting prednisolone concentration was approximately 533.3 mg/mL and the sodium deoxycholate concentration was approximately 16.67 mg/mL. 60mL of NMP concentrate was added to 2 L of water cooled to 5°C at an addition rate of 2.5 mL/min while stirring at approximately 400 rpm. The resulting suspension contained slender needle-shaped crystals less than 2 μm in width (Figure 9). The concentration contained in the precipitated suspension was 1.6% (w/v) prednisolone, 0.05% sodium deoxycholate, and 3% NMP.

The precipitated suspension was pH adjusted to 7.5-8.5 using sodium hydroxide and hydrochloric acid then homogenized (Avestin C-50 piston-gap homogenizer) for 10 passes at 10,000 psi. The NMP was removed by performing 2 successive centrifugation steps replacing the supernatant each time with a fresh surfactant solution, which contained the desired concentrations of

surfactants needed to stabilize the suspension (see Table 2). The suspension was homogenized for another 10 passes at 10,000 psi. The final suspension contained particles with a mean particle size of less than 1 μm , and 99% of particles less than 2 μm . Figure 10 is a photomicrograph of the final prednisolone suspension after homogenization.


- 5 A variety of different surfactants at varying concentrations were used in the centrifugation/surfactant replacement step (see Table 2). Table 2 lists combinations of surfactants that were stable with respect to particle size (mean < 1 μm , 99% < 2 μm), pH (6-8), drug concentration (less than 2% loss) and re-suspendability (resuspended in 60 seconds or less).

10 Figure 8: Diagram of Microprecipitation Process for Prednisolone (Examples 9-12)



Notably this process allows for adding the active compound to an aqueous diluent without the presence of a surfactant or other additive. This is a modification of process Method B in Figure 2.

Figure 9: Photomicrograph of prednisolone suspension before homogenization (Hoffman Modulation Contrast, 1250X magnification)



5 Figure 10: Photomicrograph of prednisolone suspension after homogenization (Hoffman
Modulation Contrast, 1250X magnification).




Table 2: List of stable prednisolone suspensions prepared by microprecipitation process of Figure 8 (Example 9)

			2 Weeks		2 Months						
	Initial		40°C		5°C		25°C		40°C		
Formulation	Mean	>99%	Mean	>99%	Mean	>99%	Mean	>99%	Mean	>99%	% Loss
1.6% prednisolone, 0.6% phospholipids, 0.5% sodium deoxycholate, 5 mM TRIS, 2.2% glycerol **	0.79	1.65	0.84	1.79	0.83	1.86	0.82	1.78	0.82	1.93	<2%
1.6% prednisolone, 0.6% Solutol®, 0.5% sodium deoxycholate, 2.2% glycerol	0.77	1.52	0.79	1.67	0.805	1.763	0.796	1.693	0.81	1.633	<2%
1.6% prednisolone, 0.1% poloxamer 188, 0.5% sodium deoxycholate, 2.2% glycerol	0.64	1.16	0.82	1.78	0.696	1.385	0.758	1.698	0.719	1.473	<2%
1.6% prednisolone, 5% phospholipids, 5 mM TRIS, 2.2% glycerol	0.824	1.77	0.87	1.93	0.88	1.95	0.869	1.778	0.909	1.993	<2%

* Difference in itraconazole concentration between samples stored for 2 months at 5 and 25°C.

5 ** Stable through at least 6 months.

Particle sizes (by laser light scattering), in microns:

5°C: 0.80 (mean), 1.7 (99%)

25°C: 0.90 (mean); 2.51 (99%)

40°C: 0.99 (mean); 2.03 (99%)

10 Difference in itraconazole concentration between samples stored at 5 and 25°C: <2%

Example 10: Preparation of prednisolone suspension by use of Process Category 3, Method A with homogenization.

32 g of prednisolone was dissolved into 40 mL of NMP. Gentle heating at 40-50°C was required to effect dissolution. The drug NMP concentrate was subsequently dripped at 2.5 mL/min into 2 liters of a stirred solution that consisted of 0.1.2% lecithin and 2.2% glycerin. No other surface modifiers were added. The surfactant system was buffered at pH = 8.0 with 5 mM tris buffer and the temperature was held at 0° to 5°C during the entire precipitation process. The post-precipitated dispersion was next homogenized cold (5-15 °C) for 20 passes at 10,000 psi. Following homogenization, the NMP was removed by centrifuging the suspension, removing the supernatant, and replacing the supernatant with fresh surfactant solution. This post-centrifuged suspension was then rehomogenized cold (5-15 °C) for another 20 passes at 10,000 psi. The particles produced by this process had a mean diameter of 0.927 um with 99% of the particles being less than 2.36 um.

Example 11: Preparation of nabumetone suspension by use of Process Category 3, Method B with homogenization.

Surfactant (2.2 g of poloxamer 188) was dissolved in 6 mL of N-methyl-2-pyrrolidinone. This solution was stirred at 45°C for 15 minutes, after which 1.0 g of nabumetone was added. The
5 drug dissolved rapidly. Diluent was prepared which consisted of 5 mM tris buffer with 2.2% glycerol, and adjusted to pH 8. A 100-mL portion of diluent was cooled in an ice bath. The drug concentrate was slowly added (approximately 0.8 mL/min) to the diluent with vigorous stirring. This crude suspension was homogenized at 15,000 psi for 30 minutes and then at 20,000 psi for 30 minutes (temperature = 5°C). The final nanosuspension was found to be 930 nm in effective mean
10 diameter (analyzed by laser diffraction). 99% of the particles were less than approximately 2.6 microns.

Example 12: Preparation of nabumetone suspension by use of Process Category 3, Method B with homogenization and the use of Solutol® HS 15 as the surfactant. Replacement of supernatant liquid
15 with a phospholipid medium.

Nabumetone (0.987 grams) was dissolved in 8 mL of N-methyl-2-pyrrolidinone. To this solution was added 2.2 grams of Solutol® HS 15. This mixture was stirred until complete dissolution of the surfactant in the drug concentrate. Diluent was prepared, which consisted of 5 mM tris buffer with 2.2% glycerol, and which was adjusted to pH 8. The diluent was cooled in an
20 ice bath, and the drug concentrate was slowly added (approximately 0.5 mL/min) to the diluent with vigorous stirring. This crude suspension was homogenized for 20 minutes at 15,000 psi, and for 30 minutes at 20,000 psi.

The suspension was centrifuged at 15,000 rpm for 15 minutes and the supernatant was removed and discarded. The remaining solid pellet was resuspended in a diluent consisting of 1.2% phospholipids. This medium was equal in volume to the amount of supernatant removed in the
25 previous step. The resulting suspension was then homogenized at approximately 21,000 psi for 30 minutes. The final suspension was analyzed by laser diffraction and was found to contain particles with a mean diameter of 542 nm, and a 99% cumulative particle distribution sized less than 1 micron.

30

Example 13: Preparation of 1% itraconazole suspension with poloxamer with particles of a mean diameter of approximately 220 nm

Itraconazole concentrate was prepared by dissolving 10.02 grams of itraconazole in 60 mL of N-methyl-2-pyrrolidinone. Heating to 70°C was required to dissolve the drug. The solution was
35 then cooled to room temperature. A portion of 50 mM tris(hydroxymethyl)aminomethane buffer

(tris buffer) was prepared and was pH adjusted to 8.0 with 5M hydrochloric acid. An aqueous surfactant solution was prepared by combining 22 g/L poloxamer 407, 3.0 g/L egg phosphatides, 22g/L glycerol, and 3.0 g/L sodium cholate dihydrate. 900 mL of the surfactant solution was mixed with 100 mL of the tris buffer to provide 1000 mL of aqueous diluent.

The aqueous diluent was added to the hopper of the homogenizer (APV Gaulin Model 15MR-8TA), which was cooled by using an ice jacket. The solution was rapidly stirred (4700 rpm) and the temperature was monitored. The itraconazole concentrate was slowly added, by use of a syringe pump, at a rate of approximately 2 mL/min. Addition was complete after approximately 30 minute. The resulting suspension was stirred for another 30 minutes while the hopper was still being cooled in an ice jacket, and an aliquot was removed for analysis by light microscopy any dynamic light scattering. The remaining suspension was subsequently homogenized for 15 minutes at 10,000 psi. By the end of the homogenization the temperature had risen to 74°C. The homogenized suspension was collected in a 1-L Type I glass bottle and sealed with a rubber closure. The bottle containing suspension was stored in a refrigerator at 5°C.

A sample of the suspension before homogenization showed the sample to consist of both free particles, clumps of particles, and multilamellar lipid bodies. The free particles could not be clearly visualized due to Brownian motion; however, many of the aggregates appeared to consist of amorphous, non-crystalline material.

The homogenized sample contained free submicron particles having excellent size homogeneity without visible lipid vesicles. Dynamic light scattering showed a monodisperse logarithmic size distribution with a median diameter of approximately 220 nm. The upper 99% cumulative size cutoff was approximately 500 nm. Figure 11 shows a comparison of the size distribution of the prepared nanosuspension with that of a typical parenteral fat emulsion product (10% Intralipid®, Pharmacia).




Figure 11: Comparison of size distributions of nanosuspensions (this invention) and commercial fat emulsion. (Example 13)

Example 14: Preparation of 1% itraconazole nanosuspension with hydroxyethylstarch

Preparation of Solution A: Hydroxyethylstarch (1 g, Ajinomoto) was dissolved in 3 mL of N-methyl-2-pyrrolidinone (NMP). This solution was heated in a water bath to 70-80°C for 1 hour. In another container was added 1 g of itraconazole (Wyckoff). Three mL of NMP were added and the mixture heated to 70-80°C to effect dissolution (approximately 30 minutes). Phospholipid (Lipoid S-100) was added to this hot solution. Heating was continued at 70-90°C for 30 minutes until all of the phospholipid was dissolved. The hydroxyethylstarch solution was combined with the itraconazole/ phospholipid solution. This mixture was heated for another 30 minutes at 80-95°C to dissolve the mixture.

Addition of Solution A to Tris Buffer: Ninety-four (94) mL of 50 mM tris(hydroxymethyl)aminomethane buffer was cooled in an ice bath. As the tris solution was being rapidly stirred, the hot Solution A (see above) was slowly added dropwise (less than 2 cc/minute).

After complete addition, the resulting suspension was sonicated (Cole-Parmer Ultrasonic Processor - 20,000 Hz, 80% amplitude setting) while still being cooled in the ice bath. A one-inch solid probe was utilized. Sonication was continued for 5 minutes. The ice bath was removed, the probe was removed and retuned, and the probe was again immersed in the suspension. The suspension was sonicated again for another 5 minutes without the ice bath. The sonicator probe was once again removed and retuned, and after immersion of the probe the sample was sonicated for another 5 minutes. At this point, the temperature of the suspension had risen to 82°C. The suspension was quickly cooled again in an ice bath and when it was found to be below room temperature it was poured into a Type I glass bottle and sealed. Microscopic visualization of the particles indicated individual particle sizes on the order of one micron or less.

After one year of storage at room temperature, the suspension was reevaluated for particle size and found to have a mean diameter of approximately 300 nm.

Example 15: Prophetic example of Method A using HES

The present invention contemplates preparing a 1% itraconazole nanosuspension with hydroxyethylstarch utilizing Method A by following the steps of Example 14 with the exception the HES would be added to the tris buffer solution instead of to the NMP solution. The aqueous solution may have to be heated to dissolve the HES.

Example 16: Seeding during Homogenization to Convert a Mixture of Polymorphs to the More

Stable Polymorph

Sample preparation. An itraconazole nanosuspension was prepared by a microprecipitation-homogenization method as follows. Itraconazole (3g) and Solutol HR (2.25g) were dissolved in 36mL of N-methyl-2-pyrrolidinone (NMP) with low heat and stirring to form a drug concentrate solution. The solution was cooled to room temperature and filtered through a 0.2 μ m nylon filter under vacuum to remove undissolved drug or particulate matter. The solution was viewed under polarized light to ensure that no crystalline material was present after filtering. The drug concentrate solution was then added at 1.0 mL/minute to approximately 264 mL of an aqueous buffer solution (22 g/L glycerol in 5 mM tris buffer). The aqueous solution was kept at 2-3⁰C and was continuously stirred at approximately 400 rpm during the drug concentrate addition. Approximately 100 mL of the resulting suspension was centrifuged and the solids re-suspended in a pre-filtered solution of 20% NMP in water. This suspension was re-centrifuged and the solids were transferred to a vacuum oven for overnight drying at 25⁰C. The resulting solid sample was labeled SMP 2 PRE.

Sample characterization. The sample SMP 2 PRE and a sample of the raw material itraconazole were analyzed using powder x-ray diffractometry. The measurements were performed using a Rigaku MiniFlex+ instrument with copper radiation, a step size of 0.02⁰ 2 θ and scan speed of 0.25⁰ 2 θ /minute. The resulting powder diffraction patterns are shown in Figure 12. The patterns show that SMP-2-PRE is significantly different from the raw material, suggesting the presence of a different polymorph or a pseudopolymorph.

Differential scanning calorimetry (DSC) traces for the samples are shown in Figures 13a and 13b. Both samples were heated at 2⁰/min to 180⁰C in hermetically sealed aluminum pans.

The trace for the raw material itraconazole (Figure 13a) shows a sharp endotherm at approximately 165⁰C.

The trace for SMP 2 PRE (Figure 13b) exhibits two endotherms at approximately 159⁰C and 153⁰C. This result, in combination with the powder x-ray diffraction patterns, suggests that SMP 2 PRE consists of a mixture of polymorphs, and that the predominant form is a polymorph that is less stable than polymorph present in the raw material.

Further evidence for this conclusion is provided by the DSC trace in Figure 14, which shows that upon heating SMP 2 PRE through the first transition, then cooling and reheating, the less stable polymorph melts and recrystallizes to form the more stable polymorph.

Seeding. A suspension was prepared by combining 0.2g of the solid SMP 2 PRE and 0.2g of raw material itraconazole with distilled water to a final volume of 20 mL (seeded sample). The suspension was stirred until all the solids were wetted. A second suspension was prepared in the same manner but without adding the raw material itraconazole (unseeded sample). Both suspensions were homogenized at approximately 18,000 psi for 30 minutes. Final temperature of the

suspensions after homogenization was approximately 30°C. The suspensions were then centrifuged and the solids dried for approximately 16 hours at 30°C.

Figure 15 shows the DSC traces of the seeded and unseeded samples. The heating rate for both samples was 2°/min to 180°C in hermetically sealed aluminum pans. The trace for the unseeded sample shows two endotherms, indicating that a mixture of polymorphs is still present after homogenization. The trace for the seeded sample shows that seeding and homogenization causes the conversion of the solids to the stable polymorph. Therefore, seeding appears to influence the kinetics of the transition from the less stable to the more stable polymorphic form.

10 Example 17: Seeding during Precipitation to Preferentially Form a Stable Polymorph

Sample preparation. An itraconazole-NMP drug concentrate was prepared by dissolving 1.67g of itraconazole in 10mL of NMP with stirring and gentle heating. The solution was filtered twice using 0.2 µm syringe filters. Itraconazole nanosuspensions were then prepared by adding 1.2 mL of the drug concentrate to 20 mL of an aqueous receiving solution at approx. 3°C and stirring at approx. 500 rpm. A seeded nanosuspension was prepared by using a mixture of approx. 0.02g of raw material itraconazole in distilled water as the receiving solution. An unseeded nanosuspension was prepared by using distilled water only as the receiving solution. Both suspensions were centrifuged, the supernatants decanted, and the solids dried in a vacuum oven at 30°C for approximately 16 hours.

20 Sample characterization. Figure 16 shows a comparison of the DSC traces for the solids from the seeded and unseeded suspensions. The samples were heated at 2°/min to 180°C in hermetically sealed aluminum pans. The dashed line represents the unseeded sample, which shows two endotherms, indicating the presence of a polymorphic mixture.

The solid line represents the seeded sample, which shows only one endotherm near the expected melting temperature of the raw material, indicating that the seed material induced the exclusive formation of the more stable polymorph.

Example 18: Polymorph control by seeding the drug concentrate

Sample preparation. The solubility of itraconazole in NMP at room temperature (approximately 22 °C) was experimentally determined to be 0.16 g/mL. A 0.20 g/mL drug concentrate solution was prepared by dissolving 2.0 g of itraconazole and 0.2 g Poloxamer 188 in 10 mL NMP with heat and stirring. This solution was then allowed to cool to room temperature to yield a supersaturated solution. A microprecipitation experiment was immediately performed in which 1.5 mL of the drug concentrate was added to 30 mL of an aqueous solution containing 0.1% deoxycholate, 2.2% glycerol. The aqueous solution was maintained at ~2 °C and a stir rate of 350

rpm during the addition step. The resulting presuspension was homogenized at ~13,000 psi for approx. 10 minutes at 50 °C. The suspension was then centrifuged, the supernatant decanted, and the solid crystals dried in a vacuum oven at 30 °C for 135 hours.

The supersaturated drug concentrate was subsequently aged by storing at room temperature in order to induce crystallization. After 12 days, the drug concentrate was hazy, indicating that crystal formation had occurred. An itraconazole suspension was prepared from the drug concentrate, in the same manner as in the first experiment, by adding 1.5 mL to 30 mL of an aqueous solution containing 0.1% deoxycholate, 2.2% glycerol. The aqueous solution was maintained at ~5 °C and a stir rate of 350 rpm during the addition step. The resulting presuspension was homogenized at ~13,000 psi for approx. 10 minutes at 50 °C. The suspension was then centrifuged, the supernatant decanted, and the solid crystals dried in a vacuum oven at 30 °C for 135 hours.

Sample characterization. X-ray powder diffraction analysis was used to determine the morphology of the dried crystals. The resulting patterns are shown in Figure 17. The crystals from the first experiment (using fresh drug concentrate) were determined to consist of the more stable polymorph. In contrast, the crystals from the second experiment (aged drug concentrate) were predominantly composed of the less stable polymorph, with a small amount of the more stable polymorph also present. Therefore, it is believed that aging induced the formation of crystals of the less stable polymorph in the drug concentrate, which then acted as seed material during the microprecipitation and homogenization steps such that the less stable polymorph was preferentially formed.




Figure 12: X-ray powder diffraction patterns for raw material itraconazole (top) and SMP-2-PRE (bottom). The raw material pattern has been shifted upward for clarity. (Example 16)





Figure 13a: DSC trace for raw material itraconazole (Example 16)



5 Figure 13b: DSC trace for SMP-2-PRE. (Example 16)

-36-




Figure 14: DSC trace for SMP-2-PRE showing the melt of the less stable polymorph upon heating to 160 °C, a recrystallization event upon cooling, and the subsequent melting of the more stable polymorph upon reheating to 180 °C. (Example 16)

5




Figure 15: Comparison of SMP-2-PRE samples after homogenization. Solid line = sample seeded with raw material itraconazole. Dashed line = unseeded sample. The solid line has been shifted by 1 W/g for clarity (Example 16)

10




Figure 16: Effect of seeding during precipitation. Dashed line = unseeded sample, solid line = sample seeded with raw material itraconazole. The unseeded trace (dashed line) has been shifted upward by 1.5 W/g for clarity. (Example 17)




Figure 17: Effect of seeding the drug concentrate through aging. Top x-ray diffraction pattern is for crystals prepared from fresh drug concentrate, and is consistent with the stable polymorph (see Figure 12, top). Bottom pattern is for crystals prepared from aged (seeded) drug concentrate, and is consistent with the metastable polymorph (see Figure 12, bottom). The top pattern has been shifted upward for clarity. (Example 18)

While specific embodiments have been illustrated and described, numerous modifications come to mind without departing from the spirit of the invention and the scope of protection is only limited by the scope of the accompanying claims.

CLAIMS

What is claimed is:

1. A method for preparing submicron sized particles of an organic compound, the solubility of which is greater in a water-miscible first solvent than in a second solvent which is aqueous, the process comprising the steps of:

(i) dissolving the organic compound in the water-miscible first solvent to form a solution, the first solvent being selected from the group consisting of N-methyl-2-pyrrolidinone, 2-pyrrolidone, dimethyl sulfoxide, dimethylacetamide, lactic acid, methanol, ethanol, isopropanol, 3-pentanol, n-propanol, glycerol, butylene glycol, ethylene glycol, propylene glycol, mono- and diacylated monoglycerides, dimethyl isosorbide, acetone, dimethylformamide, 1,4-dioxane, polyethylene glycol, polyethylene glycol esters, polyethylene glycol sorbitans, polyethylene glycol monoalkyl ethers, polypropylene glycol, polypropylene alginate, PPG-10 butanediol, PPG-10 methyl glucose ether, PPG-20 methyl glucose ether, PPG-15 stearyl ether, propylene glycol dicaprylate, propylene glycol dicaprate, propylene glycol laurate;

(ii) mixing the solution with the second solvent to define a pre-suspension; and

(iii) adding energy to the pre-suspension to form particles having an average effective particle size of less than about 2 μm .

2. The method of claim 1 further comprising the step of:

mixing into the second solvent a first surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and surface active biological modifiers.

3. The method of claim 2 wherein the nonionic surfactant is selected from the group consisting of: polyoxyethylene fatty alcohol ethers, polyoxyethylene sorbitan fatty acid esters, polyoxyethylene fatty acid esters, sorbitan esters, glycerol monostearate, polyethylene glycols, polypropylene glycols, cetyl alcohol, cetostearyl alcohol, stearyl alcohol, aryl alkyl polyether alcohols, polyoxyethylene-polyoxypropylene copolymers, polaxamines, methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline cellulose, polysaccharides, starch, starch derivatives, hydroxyethylstarch, polyvinyl alcohol, and polyvinylpyrrolidone.

4. The method of claim 2 wherein the anionic surfactant is selected from the group consisting of: potassium laurate, triethanolamine stearate, sodium lauryl sulfate, sodium dodecylsulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, phosphatidyl glycerol, phosphatidyl inositol, phosphatidylserine, phosphatidic acid and their salts, glyceryl esters, sodium carboxymethylcellulose, bile acids and their salts, cholic acid, deoxycholic acid, glycocholic acid, taurocholic acid, glycodeoxycholic acid, and calcium carboxymethylcellulose.

5. The method of claim 2 wherein the cationic surfactant is selected from the group consisting of quaternary ammonium compounds, benzalkonium chloride, cetyltrimethylammonium bromide,

chitosans and lauryldimethylbenzylammonium chloride.

6. The method of claim 2 wherein the surface active biological modifiers are selected from the group consisting of: albumin, casein, heparin, hirudin, or other proteins.

7. The method of claim 2 wherein the first solvent is N-methyl-2-pyrrolidinone.

5 8. The method of claim 7 wherein the anionic surfactant is a copolymer of oxyethylene and oxypropylene.

9. The method of claim 8 wherein the copolymer of oxyethylene and oxypropylene is a block copolymer.

10 10. The method of claim 2 further comprising the step of mixing into the second solvent a second surface modifier.

11. The method of claim 10 wherein the second surface modifier is selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and surface active biological modifiers.

12. The method of claim 11 wherein the second surface modifier is a bile salt or a salt thereof.

15 13. The method of claim 11 wherein the second surface modifier is selected from deoxycholic acid, glycocholic acid, glycodeoxycholic acid, taurocholic acid and salts of these acids.

14. The method of claim 2 further comprising the step of adding a pH adjusting agent to the second solvent.

20 15. The method of claim 14 wherein the pH adjusting agent is selected from the group consisting of sodium hydroxide, hydrochloric acid, tris buffer, citrate buffer, acetate, lactate, and meglumine.

16. The method of claim 14 wherein the pH adjusting agent is added to the second solvent to bring the pH of the second solvent within the range of from about 3 to about 11.

17. The method of claim 1 further comprising the step of:

25 mixing into the solution a third surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and surface active biological modifiers.

30 18 The method of claim 17 wherein the nonionic surfactant of the third surface modifier is selected from the group consisting of: polyoxyethylene fatty alcohol ethers, polyoxyethylene sorbitan fatty acid esters, polyoxyethylene fatty acid esters, sorbitan esters, glycerol monostearate, polyethylene glycols, polypropylene glycols, cetyl alcohol, cetostearyl alcohol, stearyl alcohol, aryl alkyl polyether alcohols, polyoxyethylene-polyoxypropylene copolymers, polaxamines, methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline cellulose, polysaccharides, starch, starch derivatives, hydroxyethylstarch, polyvinyl alcohol, and polyvinylpyrrolidone.

35 19. The method of claim 17 wherein the anionic surfactant of the third surface modifier is selected from the group consisting of: potassium laurate, triethanolamine stearate, sodium lauryl

sulfate, sodium dodecylsulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, phosphatidyl glycerol, phosphatidyl inositol, phosphatidylserine, phosphatidic acid and their salts, glyceryl esters, sodium carboxymethylcellulose, bile acids and their salts and calcium carboxymethylcellulose.

- 5 20. The method of claim 17 wherein the cationic surfactant of the third surface modifier is selected from the group consisting of quaternary ammonium compounds, benzalkonium chloride, cetyltrimethylammonium bromide, chitosans and lauryldimethylbenzylammonium chloride.
21. The method of claim 17 wherein the surface active biological modifiers are selected from the group consisting of: albumin, casein, heparin, hirudin, or other proteins.
- 10 22. The method of claim 17 wherein the first solvent is N-methyl-2-pyrrolidinone.
23. The method of claim 22 wherein the third surface modifier is a copolymer of oxyethylene and oxypropylene.
24. The method of claim 23 wherein the copolymer of oxyethylene and oxypropylene is a block copolymer.
- 15 25. The method of claim 17 further comprising the step of mixing into the solution a fourth surface modifier.
26. The method of claim 25 wherein the fourth surface modifier is selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and surface active biological modifiers.
- 20 27. The method of claim 26 wherein the fourth surface modifier is a nonionic surfactant is selected from the group consisting of: polyoxyethylene fatty alcohol ethers, polyoxyethylene sorbitan fatty acid esters, polyoxyethylene fatty acid esters, sorbitan esters, glycerol monostearate, polyethylene glycols, polypropylene glycols, cetyl alcohol, cetostearyl alcohol, stearyl alcohol, aryl alkyl polyether alcohols, polyoxyethylene-polyoxypropylene copolymers, polaxamines,
- 25 methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline cellulose, polysaccharides, starch, starch derivatives, hydroxyethylstarch, polyvinyl alcohol, and polyvinylpyrrolidone.
28. The method of claim 26 wherein the fourth surface modifier is an anionic surfactant selected from the group consisting of: potassium laurate, triethanolamine stearate, sodium lauryl sulfate,
- 30 sodium dodecylsulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, phosphatidyl glycerol, phosphatidyl inositol, phosphatidylserine, phosphatidic acid and their salts, glyceryl esters, sodium carboxymethylcellulose, bile acids and their salts and calcium carboxymethylcellulose.
29. The method of claim 26 wherein the fourth surface modifier is a cationic surfactant selected
- 35 from the group consisting of: of quaternary ammonium compounds, benzalkonium chloride,

cetyltrimethylammonium bromide, chitosans and lauryldimethylbenzylammonium chloride.

30. The method of claim 26 wherein the surface active biological modifiers are selected from the group consisting of: albumin, casein, heparin, hirudin, or other proteins.

31. The method of claim 17 further comprising the step of:

5 mixing into the second solvent a fifth surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and surface active biological modifiers.

32. The method of claim 31 wherein the fifth surface modifier is a nonionic surfactant selected from the group consisting of: polyoxyethylene fatty alcohol ethers, polyoxyethylene sorbitan fatty acid esters, polyoxyethylene fatty acid esters, sorbitan esters, glycerol monostearate, polyethylene glycols, polypropylene glycols, cetyl alcohol, cetostearyl alcohol, stearyl alcohol, aryl alkyl polyether alcohols, polyoxyethylene-polyoxypropylene copolymers, polaxamines, methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline cellulose, polysaccharides, starch, starch derivatives, hydroxyethylstarch, polyvinyl alcohol, and polyvinylpyrrolidone.

15 33. The method of claim 31 wherein the fifth surface modifier is an anionic surfactant selected from the group consisting of: potassium laurate, triethanolamine stearate, sodium lauryl sulfate, sodium dodecylsulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, phosphatidyl glycerol, phosphatidyl inositol, phosphatidylserine, phosphatidic acid and their salts, glyceryl esters, sodium carboxymethylcellulose, bile acids and their salts and calcium
20 carboxymethylcellulose.

34. The method of claim 31 wherein the fifth surface modifier is a cationic surfactant selected from the group consisting of quaternary ammonium compounds, benzalkonium chloride, cetyltrimethylammonium bromide, chitosans and lauryldimethylbenzylammonium chloride.

35. The method of claim 31 wherein the surface active biological modifiers are selected from the
25 group consisting of: albumin, casein, heparin, hirudin, or other proteins.

36. The method of claim 31 wherein the first solvent is N-methyl-2-pyrrolidinone.

37. The method of claim 36 wherein the fifth surface modifier is a copolymer of oxyethylene and oxypropylene.

38. The method of claim 37 wherein the copolymer of oxyethylene and oxypropylene is a block
30 copolymer.

39. The method of claim 31 further comprising the step of mixing into the solution a sixth surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and surface active biological modifiers.

40. The method of claim 1 further comprising the step of:
35 mixing into the second solvent a phospholipid.

41. The method of claim 40 wherein the phospholipid is selected from natural phospholipids and synthetic phospholipids.
42. The method of claim 40 wherein the phospholipid is selected from the group consisting of: phosphatidylcholine, phosphatidylethanolamine, phosphatidylserine, phosphatidylinositol, phosphatidylglycerol, phosphatidic acid, lysophospholipids, egg phospholipid and soybean phospholipid.
43. The method of claim 40 further comprising the step of mixing into the solution a seventh surface modifier selected from anionic surfactants, cationic surfactants and non-ionic surfactants.
44. The method of claim 43 wherein the nonionic surfactant of the seventh surface modifier is selected from the group consisting of: polyoxyethylene fatty alcohol ethers, polyoxyethylene sorbitan fatty acid esters, polyoxyethylene fatty acid esters, sorbitan esters, glycerol monostearate, polyethylene glycols, polypropylene glycols, cetyl alcohol, cetostearyl alcohol, stearyl alcohol, aryl alkyl polyether alcohols, polyoxyethylene-polyoxypropylene copolymers, polaxamines, methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline cellulose, polysaccharides, starch, starch derivatives, hydroxyethylstarch, polyvinyl alcohol, and polyvinylpyrrolidone.
45. The method of claim 43 wherein the anionic surfactant of the seventh surface modifier is selected from the group consisting of: potassium laurate, triethanolamine stearate, sodium lauryl sulfate, sodium dodecylsulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, phosphatidyl glycerol, phosphatidyl inositol, phosphatidylserine, phosphatidic acid and their salts, glyceryl esters, sodium carboxymethylcellulose, bile acids and their salts and calcium carboxymethylcellulose.
46. The method of claim 43 wherein the cationic surfactant of the seventh surface modifier is selected from the group consisting of quaternary ammonium compounds, benzalkonium chloride, cetyltrimethylammonium bromide, chitosans and lauryldimethylbenzylammonium chloride.
47. The method of claim 43 wherein the surface active biological modifiers are selected from the group consisting of: albumin, casein, heparin, hirudin, or other proteins.
48. The method of claim 43 wherein the seventh surface modifier is a bile acid or a salt thereof.
49. The method of claim 43 wherein the first solvent is N-methyl-2-pyrrolidinone.
50. The method of claim 49 further comprising the step of adding a phospholipid to the second solvent.
51. The method of claim 50 wherein the phospholipid is selected from natural phospholipids and synthetic phospholipids.
52. The method of claim 50 wherein the phospholipid is selected from the group consisting of: phosphatidylcholine, phosphatidylethanolamine, phosphatidylserine, phosphatidylinositol,

phosphatidylglycerol, phosphatidic acid, lysophospholipids, egg phospholipid and soybean phospholipid.

53. The method of claim 50 further comprising the step of mixing into the solution an eighth surface modifier selected from anionic surfactants, cationic surfactants and non-ionic surfactants.

5 54. The method of claim 53 wherein the nonionic surfactant of the eighth surface modifier is selected from the group consisting of: polyoxyethylene fatty alcohol ethers, sorbitan fatty acid esters, polyoxyethylene fatty acid esters, sorbitan esters, glycerol monostearate, polyethylene glycols, cetyl alcohol, cetostearyl alcohol, stearyl alcohol, poloxamers, polaxamines, methylcellulose, hydroxycellulose, hydroxy propylcellulose, hydroxy propylmethylcellulose, noncrystalline cellulose, polyvinyl alcohol, and polyvinylpyrrolidone.

10 55. The method of claim 53 wherein the anionic surfactant of the eighth surface modifier is selected from the group consisting of: potassium laurate, triethanolamine stearate, sodium lauryl sulfate, sodium dodecylsulfate, alkyl polyoxyethylene sulfates, sodium alginate, dioctyl sodium sulfosuccinate, phosphatidyl glycerol, phosphatidyl inositol, phosphatidylserine, phosphatidic acid and their salts, glyceryl esters, sodium carboxymethylcellulose, bile acids and their salts and calcium carboxymethylcellulose.

56. The method of claim 53 wherein the cationic surfactant of the eighth surface modifier is selected from the group consisting of quaternary ammonium compounds, benzalkonium chloride, cetyltrimethylammonium bromide, chitosans and lauryldimethylbenzylammonium chloride.

20 57. The method of claim 53 wherein the surface active biological modifiers are selected from the group consisting of: albumin, casein, heparin, hirudin, or other proteins.

58. The method of claim 53 wherein the eighth surface modifier is a bile acid or a salt thereof.

59. The method of claim 58 wherein the first solvent is N-methyl-2-pyrrolidinone.

60. A method for preparing submicron sized particles of an organic compound, the solubility of which is greater in a water-miscible first solvent than in a second solvent which is aqueous, the process comprising the steps of:

(i) dissolving the organic compound in the water-miscible first solvent to form a solution, the first solvent being selected from the group consisting of N-methyl-2-pyrrolidinone, 2-pyrrolidinone, dimethyl sulfoxide, dimethylacetamide, lactic acid, methanol, ethanol, isopropanol, 3-pentanol, n-propanol, glycerol, butylene glycol, ethylene glycol, propylene glycol, mono- and diacylated monoglycerides, dimethyl isosorbide, acetone, dimethylformamide, 1,4-dioxane, ethyl acetate, propyl acetate, polyethylene glycol, polyethylene glycol esters, polyethylene glycol sorbitans, polyethylene glycol monoalkyl ethers, polypropylene glycol, polypropylene alginate, PPG-10 butanediol, PPG-10 methyl glucose ether, PPG-20 methyl glucose ether, PPG-15 stearyl ether, propylene glycol dicaprylate, propylene glycol dicaprinate, propylene glycol laurate;

(ii) mixing the solution with the second solvent to define a pre-suspension wherein the organic compound is in an amorphous form, a semicrystalline form or in a supercooled liquid form as determined by DSC and having an average effective particle size; and

(iii) annealing the pre-suspension to form particles having essentially the same average effective particle size of the pre-suspension and in a more stable form.

61. The method of claim 60 wherein the annealing step includes the step of converting the particles of the presuspension to a crystalline form as determined by DSC.

62. The method of claim 60 wherein the particles after the annealing step have a reduced tendency to aggregate into larger particles when compared to the particles of the pre-suspension.

63. The method of claim 60 wherein the particles of the presuspension have an average effective particle size of less than about 2 μm .

64. The method of claim 60 wherein the particles of the presuspension have an average effective particle size of from about 2 μm to about 50 nm.

65. The method of claim 60 wherein the particles of the presuspension have an average effective particle size of less than about 400 nm.

66. A method for preparing submicron sized particles of an organic compound, the solubility of which is greater in a water-miscible first solvent than in a second solvent which is aqueous, the process comprising the steps of:

(i) dissolving the organic compound in the water-miscible first solvent to form a solution, the first solvent being selected from the group consisting of N-methyl-2-pyrrolidinone, 2-pyrrolidone, dimethyl sulfoxide, dimethylacetamide, lactic acid, methanol, ethanol, isopropanol, 3-pentanol, n-propanol, glycerol, butylene glycol, ethylene glycol, propylene glycol, mono- and diacylated monoglycerides, dimethyl isosorbide, acetone, dimethylformamide, 1,4-dioxane, polyethylene glycol, polyethylene glycol esters, polyethylene glycol sorbitans, polyethylene glycol monoalkyl ethers, polypropylene glycol, polypropylene alginate, PPG-10 butanediol, PPG-10 methyl glucose ether, PPG-20 methyl glucose ether, PPG-15 stearyl ether, propylene glycol dicaprylate, propylene glycol dicaprate, propylene glycol laurate;

(ii) mixing the solution with the second solvent to define a pre-suspension of particles in a friable form; and

(iii) adding energy to the pre-suspension to form particles having an average effective particle size of less than about 2 μm .

67. The method of claim 66 further comprising the step of: mixing into the second solvent a first surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and biological surface active molecules.

68. The method of claim 67 wherein the first solvent is N-methyl-2-pyrrolidinone.

69. The method of claim 68 wherein the anionic surfactant is a copolymer of oxyethylene and oxypropylene.

70. The method of claim 69 wherein the copolymer of oxyethylene and oxypropylene is a block
5 copolymer.

71. The method of claim 67 further comprising the step of mixing into the second solvent a second surface modifier selected from the group consisting of anionic surfactants, cationic surfactants, nonionic surfactants and biological surface active molecules.

72. The method of claim 71 wherein the second surface modifier is a bile salt or a salt thereof.

10 73. The method of claim 71 wherein the second surface modifier is selected from deoxycholic acid, glycocholic acid, glycodeoxycholic acid, taurocholic acid and salts of these acids.

74. The method of claim 67 further comprising the step of adding a pH adjusting agent to the second solvent.

15 75. The method of claim 74 wherein the pH adjusting agent is selected from the group consisting of sodium hydroxide, hydrochloric acid, tris buffer, citrate buffer, acetate, lactate, and meglumine.

76. The method of claim 74 wherein the pH adjusting agent is added to the second solvent to bring the pH of the second solvent within the range of from about 3 to about 11.

77. The method of claim 66 further comprising the step of:

20 mixing into the solution a third surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and biological surface active molecules.

78. The method of claim 77 wherein the first solvent is N-methyl-2-pyrrolidinone.

79. The method of claim 78 wherein the third surface modifier is a copolymer of oxyethylene and oxypropylene.

25 80. The method of claim 79 wherein the copolymer of oxyethylene and oxypropylene is a block copolymer.

81. The method of claim 77 further comprising the step of mixing into the solution a fourth surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and biological surface active molecules.

30 82. The method of claim 77 further comprising the step of:

mixing into the second solvent a fifth surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and biological surface active molecules.

83. The method of claim 82 wherein the first solvent is N-methyl-2-pyrrolidinone.

35 84. The method of claim 83 wherein the fifth surface modifier is a copolymer of oxyethylene and

oxypropylene.

85. The method of claim 82 further comprising the step of mixing into the solution a sixth surface modifier selected from the group consisting of: anionic surfactants, cationic surfactants, nonionic surfactants and biological surface active molecules.

5 86. The method of claim 66 further comprising the step of:
mixing into the second solvent a phospholipid.

87. The method of claim 86 wherein the phospholipid is selected from natural phospholipids and synthetic phospholipids.

10 88. The method of claim 86 wherein the phospholipid is selected from the group consisting of:
phosphatidylcholine, phosphatidylethanolamine, phosphatidylserine, phosphatidylinositol,
phosphatidylglycerol, phosphatidic acid, lysophospholipids, egg phospholipid and soybean
phospholipid.

15 89. The method of claim 86 further comprising the step of mixing into the solution a seventh
surface modifier selected from anionic surfactants, cationic surfactants, non-ionic surfactants and
biological surface active molecules.

90. The method of claim 89 wherein the seventh surface modifier is a bile acid or a salt thereof.

91. The method of claim 90 wherein the first solvent is N-methyl-2-pyrrolidinone.

92. The method of claim 91 further comprising the step of adding a phospholipid to the second
solvent.

20 93. The method of claim 92 wherein the phospholipid is selected from natural phospholipids and
synthetic phospholipids.

25 94. The method of claim 92 wherein the phospholipid is selected from the group consisting of:
phosphatidylcholine, phosphatidylethanolamine, phosphatidylserine, phosphatidylinositol,
phosphatidylglycerol, phosphatidic acid, lysophospholipids, egg phospholipid and soybean
phospholipid.

95. The method of claim 92 further comprising the step of mixing into the solution an eighth
surface modifier selected from anionic surfactants, cationic surfactants, non-ionic surfactants and
biological surface active molecules.

96. The method of claim 95 wherein the eighth surface modifier is a bile acid or a salt thereof.

30 97. The method of claim 96 wherein the first solvent is N-methyl-2-pyrrolidinone.

98. A method for preparing a suspension of a pharmaceutically-active compound, the solubility
of which is greater in a water-miscible first organic solvent than in a second solvent which is
aqueous, the process comprising the steps of:

(i) dissolving a first quantity of the pharmaceutically-active compound in the water-

miscible first organic solvent to form a first solution;

(ii) mixing the first solution with the second solvent to precipitate the pharmaceutically-active compound to create a presuspension; and

(iii) seeding the first solution or the second solvent prior to the or the presuspension after
5 the mixing step.

99. The method of claim 98 wherein the step of precipitating the pharmaceutically-active compound comprises the step of precipitating the compound in a form selected from the group consisting of a supercooled liquid, an amorphous particle, a semicrystalline particle and a crystalline particle.

10 100. The method of claim 99 further comprising the step of adding energy to the presuspension.

101. The method of claim 100 wherein the adding-energy step comprises the step of subjecting the presuspension to high energy agitation.

102. The method of claim 100 wherein the adding-energy step comprises the step of adding heat to the presuspension.

15 103. The method of claim 100 wherein the energy-addition step comprises the step of exposing the presuspension to electromagnetic energy.

104. The method of claim 103 wherein the step of exposing the presuspension to electromagnetic energy comprises the step of exposing the presuspension to a laser beam.

105. The method of claim 98 further comprising the step of forming a desired polymorph of the
20 pharmaceutically active compound.

106. The method of claim 105 wherein the step of seeding comprises the step of using a seed compound.

107. The method of claim 105 wherein the seed compound is the desired polymorph of the pharmaceutically-active compound.

25 108. The method of claim 105 wherein the seed compound is a compound other than the desired polymorph of the pharmaceutically-active compound.

109. The method of claim 108 wherein the seed compound is selected from the group consisting of: an inert impurity; and an organic compound with a structure similar to that of the desired polymorph.

30 110. The method of claim 105 wherein the seed compound is added to the first solution.

111. The method of claim 105 wherein the seed compound is added to the second solvent.

112. The method of claim 105 wherein the seed compound is added to the presuspension.

113. The method of claim 104 wherein the step of forming a desired polymorph comprises the step of forming a seed compound in the first solution.

114. The method of claim 113 wherein the step of forming the seed compound in the first solution comprises the step of adding the pharmaceutically-active compound in sufficient quantity to exceed the solubility of the pharmaceutically-active compound in the first solvent to create a supersaturated solution.
- 5 115. The method of claim 114 wherein the step of forming the seed compound in the first solution further comprises the step of treating the supersaturated solution.
116. The method of claim 115 wherein the step of treating the supersaturated solution comprises the step of aging the supersaturated solution.
117. The method of claim 116 wherein the seeding step comprises the step of using
10 electromagnetic energy.
118. The method of claim 117 wherein the electromagnetic energy is dynamic electromagnetic energy.
119. The method of claim 117 wherein the electromagnetic energy is a laser beam.
120. The method of claim 117 wherein the electromagnetic energy is radiation.
- 15 121. The method of claim 98 wherein the step of seeding comprises the step of using a particle beam.
122. The method of claim 98 wherein the step of seeding comprises the step of using an electron beam.
123. The method of claim 98 wherein the step of seeding comprises using ultrasound.
- 20 124. The method of claim 98 wherein the step of seeding comprises using a static electrical field.
125. The method of claim 98 wherein the step of seeding comprises using a static magnetic field.
126. The method of claim 98 further comprising the steps of forming particles having an average effective particle size less than about $2\mu\text{m}$.
127. A composition of matter of a polymorphic pharmaceutically-active compound in a desired
25 polymorphic form essentially free of an unspecified polymorphic form.
128. The composition of claim 127 wherein the pharmaceutically-active compound is itraconazole.

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 July 2002 (18.07.2002)

PCT

(10) International Publication Number
WO 02/055059 A3

(51) International Patent Classification⁷: **A61K 9/20**,
9/51, 31/496

WERLING, Jane; 605 S. Highland, Arlington Heights,
IL 60005 (US). **SRIRAM, Rajaram**; 3014 Knollwood,
Glenview, IL 60025 (US).

(21) International Application Number: PCT/US01/49737

(74) Agent: **BUONAIUTO, Mark, J.**; Baxter International
Inc., One Baxter Parkway, Deerfield, IL 60015 (US).

(22) International Filing Date:
20 December 2001 (20.12.2001)

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, PH, PL, PT, RO, RU, SD, SE, SG, SI,
SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA,
ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/258,160 22 December 2000 (22.12.2000) US
09/874,799 5 June 2001 (05.06.2001) US
09/874,637 5 June 2001 (05.06.2001) US
09/874,499 5 June 2001 (05.06.2001) US
09/953,979 17 September 2001 (17.09.2001) US
10/035,821 19 October 2001 (19.10.2001) US
10/021,692 12 December 2001 (12.12.2001) US

(84) Designated States (*regional*): European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE, TR).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(71) Applicant: **BAXTER INTERNATIONAL INC.**
[US/US]; One Baxter Parkway, Deerfield, IL 60015 (US).

(88) Date of publication of the international search report:
6 September 2002

(72) Inventors: **KIPP, James, E.**; 609 Hermosa Avenue,
Wauconda, IL 60084 (US). **WONG, Joseph, Chung,**
Tak; 36141 N. Bridlewood Avenue, Gurnee, IL 60031
(US). **DOTY, Mark, J.**; 610 Kenilworth, Grayslake, IL
60030 (US). **REBBECK, Christine, L.**; 525 Eagle Ridge
Lane, Algonquin, IL 60102 (US). **BRYNJELSEN, Sean**;
4 Walnut Grove Ct., Lake-In-The-Hills, IL 60156 (US).

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: METHOD FOR PREPARING SUBMICRON PARTICLE SUSPENSIONS

(57) Abstract: The present invention provides a method for preparing a suspension of a pharmaceutically-active compound, the solubility of which is greater in a water-miscible first organic solvent than in a second solvent which is aqueous. The process includes the steps of : (i) dissolving a first quantity of the pharmaceutically-active compound in the water-miscible first organic solvent to form a first solution ; (ii) mixing the first solution with the second solvent to precipitate the pharmaceutically-active compound ; and (iii) seeding the first solution or the second solvent or the presuspension.

WO 02/055059 A3



INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/49737

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61K9/20 A61K9/51 A61K31/496

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 169 618 A (STERILIZATION TECHN SERV) 29 January 1986 (1986-01-29) page 6, paragraph 2 page 10, paragraph 5 page 11, line 18 -page 12, line 1 page 12, line 17 - line 30 page 14, line 9 - line 14 examples 1-16,19-28 page 29, line 22 -page 30, line 15 claims 1,,13,15,19,306-10	1-3,6-9, 60-63, 66-70
X	US 4 606 940 A (FRANK SYLVAN G ET AL) 19 August 1986 (1986-08-19) examples 1-3 claims 1,4	1,2,6, 60,66,67
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the International filing date but later than the priority date claimed

- *T* later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *A* document member of the same patent family

Date of the actual completion of the International search

3 July 2002

Date of mailing of the International search report

09/07/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Giacobbe, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/49737

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 780 062 A (LOEFROTH JAN-ERIK ET AL) 14 July 1998 (1998-07-14) the whole document	1-7, 10-13, 60,62, 63, 66-68, 71-73, 98-100
X	US 4 826 689 A (VIOLANTO MICHAEL R) 2 May 1989 (1989-05-02) abstract figures 4,6 column 6, line 41 - line 55; examples 1-28 claims 1,8,18,27,28,30,31	1,2,6-9, 60-70
X	US 5 145 684 A (LIVERSIDGE GARY G ET AL) 8 September 1992 (1992-09-08) column 2, line 37 - line 43 column 3, line 32 - line 37 column 5, line 50 - column 6, line 31	127
X	column 8, line 21 - line 32 examples 1-4,9,11-14	1-126
X	WO 99 16443 A (LARMA ILKKA ;ANTILA SAILA (FI); HARJULA MAARIT (FI); LEHTONEN LASS) 8 April 1999 (1999-04-08) abstract	127
X	US 5 122 543 A (KHANNA SATISH C) 16 June 1992 (1992-06-16) the whole document	127
A	WO 98 57967 A (CHA BONG JIN ;KIM SU EON (KR); OH JUN GYO (KR); DONG A PHARMACEUTI) 23 December 1998 (1998-12-23) abstract	128
A	WO 99 33467 A (CHOONGWAE PHARMA CORP ;HONG JI WOONG (KR); LEE SANG HEON (KR); PAR) 8 July 1999 (1999-07-08) the whole document	128
A	US 6 039 981 A (WOO JONG-SOO ET AL) 21 March 2000 (2000-03-21) the whole document	128

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 01/49737

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☒ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
see FURTHER INFORMATION sheet PCT/ISA/210
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

Continuation of Box I.2

The initial phase of the search revealed a very large number of documents relevant to the issue of novelty. So many documents were retrieved that it is impossible to determine which parts of the claim(s) may be said to define subject-matter for which protection might legitimately be sought (Article 6 PCT). It is in particular observed that present claim 1 refers to a method of purifying any organic compound by a method which is standard procedure in any laboratory, namely the one involving dissolving it in a solvent where it is soluble and adding the resulting solution to a solvent where the compound is less soluble so that it precipitates, the size of the resulting particles introducing a very limited restriction. Such a method is of daily use in any laboratory, so that the number of documents disclosing it is virtually infinite, let alone the extent of its prior use. For these reasons a meaningful search over the whole breadth of the claim(s) is impossible. Consequently the search has been restricted to the use of the method in the field of purification of pharmaceutically active ingredients, in particular as far as the compounds named in the examples and in the claims are concerned.

A similar reasoning applies to claim 127, which claims any polymorphic form of any conceivable therapeutic agent. Also this claim has therefore been searched by referring only to the compounds named in the examples and in the claims.

It is further observed that the application as filed does not disclose any other form of "adding energy" than stirring during step (ii) and, in some cases, sonicating. In this respect it is not considered that "homogenizing" constitutes a form of addition of energy. Furthermore it appears from the examples provided that sonicating itself is not in many cases very effective. It is concluded that the present claims do not fulfill the requirements of Art 5 EPC. Only the aforementioned forms of "adding energy", i.e. stirring and sonicating, have been searched.

The attention of the Applicant is drawn to the fact that no examination shall be carried out for claims or parts of claims directed to subject-matter which has not been object of a Search. This applies both to the International Phase under Chapter II PCT and to the regional phase before the EPO.

The applicant's attention is drawn to the fact that claims, or parts of claims, relating to inventions in respect of which no international search report has been established need not be the subject of an international preliminary examination (Rule 66.1(e) PCT). The applicant is advised that the EPO policy when acting as an International Preliminary Examining Authority is normally not to carry out a preliminary examination on matter which has not been searched. This is the case irrespective of whether or not the claims are amended following receipt of the search report or during any Chapter II procedure.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/49737

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0169618	A	29-01-1986	CA 2089075 A1	22-02-1992
			AU 579166 B2	17-11-1988
			AU 4501285 A	22-01-1987
			CA 1282405 A1	02-04-1991
			EP 0169618 A2	29-01-1986
			EP 0544657 A1	09-06-1993
			JP 1973762 C	27-09-1995
			JP 7002209 B	18-01-1995
			JP 62027032 A	05-02-1987
			JP 6501872 T	03-03-1994
			PT 80494 A	22-11-1985
			WO 9203380 A1	05-03-1992
			US 4997454 A	05-03-1991
			US 4826689 A	02-05-1989
			AT 55921 T	15-09-1990
			DE 3579385 D1	04-10-1990
			ES 543354 D0	01-06-1986
			ES 8607007 A1	01-11-1986
			IL 75250 A	31-08-1988
			NZ 212151 A	30-08-1988
			PT 80494 B	19-08-1987
US 4606940	A	19-08-1986	AT 109974 T	15-09-1994
			AU 588275 B2	14-09-1989
			AU 5307586 A	22-07-1986
			CA 1239838 A1	02-08-1988
			DE 3587908 D1	22-09-1994
			DE 3587908 T2	05-01-1995
			DK 359186 A	29-07-1986
			EP 0207134 A1	07-01-1987
			ES 550244 D0	01-08-1987
			ES 8707424 A1	16-10-1987
			FI 863372 A ,B,	20-08-1986
			HU 40912 A2	30-03-1987
			HU 204695 B	28-02-1992
			IL 77184 A	15-08-1989
			JP 6011395 B	16-02-1994
			JP 62501198 T	14-05-1987
			KR 9301803 B1	13-03-1993
			NO 863286 A ,B,	14-08-1986
			NZ 214598 A	24-02-1989
			PH 21226 A	21-08-1987
			WO 8603676 A1	03-07-1986
US 5780062	A	14-07-1998	AT 213625 T	15-03-2002
			AU 700644 B2	14-01-1999
			AU 3885195 A	06-06-1996
			BR 9509720 A	21-10-1997
			CA 2203512 A1	23-05-1996
			CN 1165478 A	19-11-1997
			CZ 9701295 A3	17-12-1997
			DE 69525639 D1	04-04-2002
			DK 788350 T3	29-04-2002
			EE 9700214 A	15-04-1998
			EP 0788350 A1	13-08-1997
			FI 971947 A	07-05-1997
			HU 77629 A2	29-06-1998
			JP 10508840 T	02-09-1998

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/49737

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5780062 A		NO 971986 A	29-04-1997
		NZ 295497 A	27-05-1998
		PL 320425 A1	29-09-1997
		WO 9614833 A1	23-05-1996
		SK 55997 A3	14-01-1998
		TR 960406 A2	21-06-1996
		ZA 9509386 A	09-05-1996
US 4826689 A	02-05-1989	CA 2089075 A1	22-02-1992
		US 4997454 A	05-03-1991
		AU 579166 B2	17-11-1988
		AU 4501285 A	22-01-1987
		CA 1282405 A1	02-04-1991
		EP 0169618 A2	29-01-1986
		EP 0544657 A1	09-06-1993
		JP 1973762 C	27-09-1995
		JP 7002209 B	18-01-1995
		JP 62027032 A	05-02-1987
		JP 6501872 T	03-03-1994
		PT 80494 A	22-11-1985
		WO 9203380 A1	05-03-1992
		AT 55921 T	15-09-1990
		DE 3579385 D1	04-10-1990
		ES 543354 D0	01-06-1986
		ES 8607007 A1	01-11-1986
		IL 75250 A	31-08-1988
		NZ 212151 A	30-08-1988
		PT 80494 B	19-08-1987
US 5145684 A	08-09-1992	AT 184202 T	15-09-1999
		AT 195416 T	15-09-2000
		AU 642066 B2	07-10-1993
		AU 1014592 A	30-07-1992
		AU 654836 B2	24-11-1994
		AU 1014792 A	30-07-1992
		CA 2059431 A1	26-07-1992
		CA 2059432 A1	26-07-1992
		DE 69229925 D1	14-10-1999
		DE 69229925 T2	17-02-2000
		DE 69231345 D1	21-09-2000
		DE 69231345 T2	26-04-2001
		DK 498482 T3	27-03-2000
		DK 499299 T3	02-01-2001
		EP 0498482 A2	12-08-1992
		EP 0499299 A2	19-08-1992
		ES 2139586 T3	16-02-2000
		ES 2149164 T3	01-11-2000
		FI 920321 A	26-07-1992
		FI 920322 A	26-07-1992
		GR 3032059 T3	31-03-2000
		HU 62462 A2	28-05-1993
		HU 60635 A2	28-10-1992
		IE 920217 A1	29-07-1992
		IE 920218 A1	29-07-1992
		IL 100754 A	16-10-1996
		IL 100755 A	08-12-1995
		JP 4317053 A	09-11-1992
		JP 4295420 A	20-10-1992

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/49737

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5145684	A	KR 200061 B1	15-06-1999
		MX 9200291 A1	01-10-1992
		MX 9200292 A1	01-10-1992
		NO 920333 A	27-07-1992
		NO 303668 B1	17-08-1998
		NZ 241361 A	25-06-1993
		NZ 241362 A	25-06-1993
		PT 499299 T	31-01-2001
		SG 55104 A1	21-12-1998
		RU 2074002 C1	27-02-1997
		RU 2066553 C1	20-09-1996
		US 5451393 A	19-09-1995
		US 5494683 A	27-02-1996
		US 5552160 A	03-09-1996
		US 5399363 A	21-03-1995
		US 5318767 A	07-06-1994
WO 9916443	A 08-04-1999	FI 973804 A	27-03-1999
		AU 732489 B2	26-04-2001
		AU 9350698 A	23-04-1999
		BG 104250 A	29-12-2000
		BR 9813213 A	29-08-2000
		CA 2304702 A1	08-04-1999
		CN 1271282 T	25-10-2000
		EE 200000187 A	16-04-2001
		EP 1014987 A1	05-07-2000
		WO 9916443 A1	08-04-1999
		HR 20000171 A1	31-12-2000
		HU 0003757 A2	28-05-2001
		JP 2001517702 T	09-10-2001
		NO 20001585 A	27-03-2000
		NZ 503207 A	27-04-2001
		PL 339461 A1	18-12-2000
		SK 3842000 A3	12-09-2000
		TR 200000635 T2	21-09-2000
		US 6355269 B1	12-03-2002
US 5122543	A 16-06-1992	AT 94390 T	15-10-1993
		AU 619178 B2	23-01-1992
		AU 1555888 A	10-11-1988
		CA 1328219 A1	05-04-1994
		DD 269784 A5	12-07-1989
		DE 3884044 D1	21-10-1993
		DK 238888 A	05-11-1988
		EP 0289977 A1	09-11-1988
		ES 2043716 T3	01-01-1994
		FI 882044 A	05-11-1988
		HU 46847 A2	28-12-1988
		IE 63081 B	22-03-1995
		IL 86211 A	29-03-1992
		JP 1131117 A	24-05-1989
		KR 9606059 B1	08-05-1996
		MX 11339 A	01-12-1993
		NO 881933 A	07-11-1988
		NZ 224476 A	26-09-1990
		PH 24895 A	26-12-1990
		PT 87381 A ,B	31-05-1989
		ZA 8803135 A	07-11-1988

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 01/49737

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9857967	A	23-12-1998	AT 216699 T	15-05-2002
			AU 7939298 A	04-01-1999
			BR 9810124 A	08-08-2000
			CN 1262682 T	09-08-2000
			DE 69805070 D1	29-05-2002
			DK 991646 T3	10-06-2002
			EP 0991646 A1	12-04-2000
			HU 0004050 A2	28-06-2001
			JP 2002504930 T	12-02-2002
			WO 9857967 A1	23-12-1998
			PL 338631 A1	06-11-2000
			US 6346533 B1	12-02-2002
WO 9933467	A	08-07-1999	AU 1511399 A	19-07-1999
			BR 9814729 A	08-01-2002
			CA 2317106 A1	08-07-1999
			CN 1285746 T	28-02-2001
			EP 1039909 A1	04-10-2000
			JP 2001527044 T	25-12-2001
			WO 9933467 A1	08-07-1999
			PL 341566 A1	23-04-2001
			TR 200001880 T2	21-11-2000
US 6039981	A	21-03-2000	AU 5114400 A	02-01-2001
			EP 1185273 A1	13-03-2002
			WO 0076520 A1	21-12-2000
			SI 20677 A	30-04-2002
			TR 200103681 T2	21-05-2002